

BASF Ultramid® B36 01 PA6 (Dry)

Category : Polymer , Thermoplastic , Nylon , Nylon 6 , Nylon 6 , Unreinforced

Material Notes:

Ultramid B36 01 is an intermediate viscosity, PA6 grade. It conforms to FDA requirements including, 21 CFR 177.1500,EU Directive 2002/72/EC, the German BfR recommendation "X Polyamide", 1.6.1998 or legislations for other countries will be provided on request.

Order this product through the following link:

http://www.lookpolymers.com/polymer_BASF-Ultramid-B36-01-PA6-Dry.php

Physical Properties	Metric	English	Comments
Density	1.13 g/cc	0.0408 lb/in ³	ISO 1183
Water Absorption	9.5 %	9.5 %	ISO 62
Moisture Absorption at Equilibrium	2.6 %	2.6 %	23°C/50% R.H.; ISO 62
Relative Viscosity	3.6 cP	3.6 cP	ISO Test; 96 % SAV
Viscosity Test	218 cm ³ /g	218 cm ³ /g	Viscosity number

Thermal Properties	Metric	English	Comments
Melting Point	220 °C	428 °F	10 K/min

Descriptive Properties	Value	Comments
Color	Natural	
Commercial Status	North America and Europe	
FDA	21 CFR 177.1500	
Impact Modified	No	
Primary Processing Technique	Film Extrusion	

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.comEmail : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China