

## BASF Ultramid® B36 LNV PA6

Category : Polymer , Thermoplastic , Nylon , Nylon 6 , Nylon 6 , Unreinforced

**Material Notes:**

Information provided by BASF

Order this product through the following link:

[http://www.lookpolymers.com/polymer\\_BASF-Ultramid-B36-LNV-PA6.php](http://www.lookpolymers.com/polymer_BASF-Ultramid-B36-LNV-PA6.php)

Physical Properties	Metric	English	Comments
Bulk Density	0.640 - 0.740 g/cc	0.0231 - 0.0267 lb/in <sup>3</sup>	
Density	1.12 - 1.15 g/cc	0.0405 - 0.0415 lb/in <sup>3</sup>	ISO 1183

Thermal Properties	Metric	English	Comments
Melting Point	220 °C	428 °F	DIN 53765
Decomposition Temperature	>= 300 °C	>= 572 °F	

Descriptive Properties	Value	Comments
Commercial Status	Europe	
Ignition Temperature	>400°C	ASTM D1929

## Contact Songhan Plastic Technology Co.,Ltd.

Website : [www.lookpolymers.com](http://www.lookpolymers.com)Email : [sales@lookpolymers.com](mailto:sales@lookpolymers.com)

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China