

## BASF Ultramid® B3EG6 BK00564 30% Glass Filled PA6 (Dry)

Category : Polymer , Thermoplastic , Nylon , Nylon 6 , Nylon 6 , 30% Glass Fiber Filled

### Material Notes:

Ultramid B3EG6 BK00564 is a 30% glass fiber reinforced, pigmented black injection molding PA6 grade. It conforms to FDA requirements of 21 CFR 177.1500.

Order this product through the following link:

[http://www.lookpolymers.com/polymer\\_BASF-Ultramid-B3EG6-BK00564-30-Glass-Filled-PA6-Dry.php](http://www.lookpolymers.com/polymer_BASF-Ultramid-B3EG6-BK00564-30-Glass-Filled-PA6-Dry.php)

Physical Properties	Metric	English	Comments
Density	1.36 g/cc	0.0491 lb/in <sup>3</sup>	ISO 1183
Water Absorption	6.3 - 6.9 %	6.3 - 6.9 %	ISO 62
Moisture Absorption at Equilibrium	1.9 - 2.3 %	1.9 - 2.3 %	23°C/50% R.H.; ISO 62
Viscosity Measurement	140	140	Viscosity Number; ISO 307
Linear Mold Shrinkage	0.0035 cm/cm	0.0035 in/in	
Melt Flow	68 g/10 min @Load 5.00 kg, Temperature 275 °C	68 g/10 min @Load 11.0 lb, Temperature 527 °F	ISO 1133

Mechanical Properties	Metric	English	Comments
Tensile Strength, Yield	185 MPa	26800 psi	50mm/min; ISO 527
Elongation at Yield	3.5 %	3.5 %	50mm/min; ISO 527
Modulus of Elasticity	9.50 GPa	1380 ksi	ISO 527
Flexural Strength	270 MPa	39200 psi	ISO 178
Flexural Modulus	8.60 GPa	1250 ksi	ISO 178
Izod Impact, Notched (ISO)	1.50 kJ/m <sup>2</sup>	0.714 ft-lb/in <sup>2</sup>	ISO 180/A
Charpy Impact Unnotched	9.50 J/cm <sup>2</sup>	45.2 ft-lb/in <sup>2</sup>	ISO 179/1eU
	8.00 J/cm <sup>2</sup> @Temperature -30.0 °C	38.1 ft-lb/in <sup>2</sup> @Temperature -22.0 °F	ISO 179/1eU
Charpy Impact, Notched	1.50 J/cm <sup>2</sup>	7.14 ft-lb/in <sup>2</sup>	ISO 179/1eA
	1.10 J/cm <sup>2</sup> @Temperature -30.0 °C	5.24 ft-lb/in <sup>2</sup> @Temperature -22.0 °F	ISO 179/1eA

Thermal Properties	Metric	English	Comments
CTE, linear, Parallel to Flow	20.0 - 25.0 $\mu\text{m}/\text{m}\cdot\text{°C}$	11.1 - 13.9 $\mu\text{in}/\text{in}\cdot\text{°F}$	ISO 11359-1/-2
	@Temperature 23.0 - 80.0 $\text{°C}$	@Temperature 73.4 - 176 $\text{°F}$	
CTE, linear, Transverse to Flow	60.0 - 70.0 $\mu\text{m}/\text{m}\cdot\text{°C}$	33.3 - 38.9 $\mu\text{in}/\text{in}\cdot\text{°F}$	ISO 11359-1/-2
	@Temperature 23.0 - 80.0 $\text{°C}$	@Temperature 73.4 - 176 $\text{°F}$	
Specific Heat Capacity	1.50 $\text{J}/\text{g}\cdot\text{°C}$	0.359 $\text{BTU}/\text{lb}\cdot\text{°F}$	
Thermal Conductivity	0.360 $\text{W}/\text{m}\cdot\text{K}$	2.50 $\text{BTU}\cdot\text{in}/\text{hr}\cdot\text{ft}^2\cdot\text{°F}$	DIN 52612
Melting Point	220 $\text{°C}$	428 $\text{°F}$	DIN 53765
Maximum Service Temperature, Air	135 $\text{°C}$	275 $\text{°F}$	for 50% loss of tensile strength after 20,000 hr
	165 $\text{°C}$	329 $\text{°F}$	for 50% loss of tensile strength after 5,000 hr
	200 $\text{°C}$	392 $\text{°F}$	
Deflection Temperature at 0.46 MPa (66 psi)	220 $\text{°C}$	428 $\text{°F}$	ISO 75
Deflection Temperature at 1.8 MPa (264 psi)	210 $\text{°C}$	410 $\text{°F}$	ISO 75
Flammability, UL94	HB	HB	
	@Thickness 1.60 mm	@Thickness 0.0630 in	

Electrical Properties	Metric	English	Comments
Volume Resistivity	1.00e+14 $\text{ohm}\cdot\text{cm}$	1.00e+14 $\text{ohm}\cdot\text{cm}$	IEC 60093
Dielectric Constant	3.8	3.8	IEC 60250
	@Frequency 1.00e+6 Hz	@Frequency 1.00e+6 Hz	
Dissipation Factor	0.023	0.023	IEC 60250
	@Frequency 1.00e+6 Hz	@Frequency 1.00e+6 Hz	
Comparative Tracking Index	575 V	575 V	IEC 60112

Processing Properties	Metric	English	Comments
Melt Temperature	270 - 290 $\text{°C}$	518 - 554 $\text{°F}$	Injection-molding/Extrusion
Mold Temperature	80.0 - 90.0 $\text{°C}$	176 - 194 $\text{°F}$	Injection-molding

Descriptive Properties	Value	Comments
Color	BK00564	
Commercial Status	North America and Europe	
Impact Modified	No	
Primary Processing Technique	Injection Molding	

## Contact Songhan Plastic Technology Co.,Ltd.

Website : [www.lookpolymers.com](http://www.lookpolymers.com)

Email : [sales@lookpolymers.com](mailto:sales@lookpolymers.com)

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China