

## BASF Ultramid® B3WG6 HP BK 23210 30% Glass Filled PA6 (Dry)

Category : Polymer , Thermoplastic , Nylon , Nylon 6 , Nylon 6 , 30% Glass Fiber Filled

### Material Notes:

Description: 30% Glass fiber reinforced and heat aging resistant injection molding grade with enhances flowability used e.g. for automobile manifold. Information provided by BASF

Order this product through the following link:

[http://www.lookpolymers.com/polymer\\_BASF-Ultramid-B3WG6-HP-BK-23210-30-Glass-Filled-PA6-Dry.php](http://www.lookpolymers.com/polymer_BASF-Ultramid-B3WG6-HP-BK-23210-30-Glass-Filled-PA6-Dry.php)

Physical Properties	Metric	English	Comments
Bulk Density	0.500 - 0.800 g/cc	0.0181 - 0.0289 lb/in <sup>3</sup>	
Density	1.36 g/cc	0.0491 lb/in <sup>3</sup>	ISO 1183
Linear Mold Shrinkage	0.0030 cm/cm	0.0030 in/in	
Linear Mold Shrinkage, Flow	0.0025 cm/cm	0.0025 in/in	ISO 2577
	0.0025 cm/cm	0.0025 in/in	ISO 2577
Linear Mold Shrinkage, Transverse	0.0065 cm/cm	0.0065 in/in	ISO 2577
	0.0065 cm/cm	0.0065 in/in	ISO 2577
Melt Flow	68 g/10 min @Load 5.00 kg, Temperature 275 °C	68 g/10 min @Load 11.0 lb, Temperature 527 °F	ISO 1133

Thermal Properties	Metric	English	Comments
Melting Point	220 °C	428 °F	DIN 58765
Decomposition Temperature	>= 300 °C	>= 572 °F	

Processing Properties	Metric	English	Comments
Processing Temperature	80.0 °C	176 °F	Hopper Throat
Zone 1	260 °C	500 °F	Feed Zone
Zone 2	270 °C	518 °F	Compression
Zone 3	280 °C	536 °F	Metering-zone
Zone 4	280 °C	536 °F	Nozzle
Melt Temperature	270 - 290 °C	518 - 554 °F	Injection Molding/Extrusion
	280 °C	536 °F	Optimal

Processing Properties	Metric	English	Comments
	80.0 - 90.0 °C	176 - 194 °F	Injection Molding
Drying Temperature	80.0 °C	176 °F	
Dry Time	4 hour	4 hour	

Descriptive Properties	Value	Comments
Color	BK 23210	
Commercial Status	Europe	
Ignition Temperature	>400°C	ASTM D1929
Peripheral screw speed	< 0.3 m/s	

## Contact Songhan Plastic Technology Co.,Ltd.

Website : [www.lookpolymers.com](http://www.lookpolymers.com)

Email : [sales@lookpolymers.com](mailto:sales@lookpolymers.com)

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China