

BASF Ultramid® KR 4355 G7 BK 00564 35% Glass Filled PA6/6T (Conditioned)

Category : Polymer , Thermoplastic , Nylon , Nylon 6 , Nylon 6 , 40% Glass Fiber Filled

Material Notes:

Description: 35% glass-fiber reinforced product for injection-molding; high toughness, strength and stiffness, low water absorption, high melting point (295°C [563°F]). The mechanical properties remain constant after moisture absorption up to a temperature of 60°C [140°F], for instance, for automotive valve housings. Information provided by BASF

Order this product through the following link:

http://www.lookpolymers.com/polymer_BASF-Ultramid-KR-4355-G7-BK-00564-35-Glass-Filled-PA66T-Conditioned.php

Physical Properties	Metric	English	Comments
Bulk Density	0.500 - 0.800 g/cc	0.0181 - 0.0289 lb/in ³	
Density	1.43 g/cc	0.0517 lb/in ³	ISO 1183
Water Absorption	4.3 - 5.3 %	4.3 - 5.3 %	Saturation; ISO 62
Moisture Absorption at Equilibrium	0.80 - 1.2 %	0.80 - 1.2 %	23°C; 50% RH; ISO 62
Viscosity Measurement	130	130	ISO 307
Linear Mold Shrinkage	0.0035 cm/cm	0.0035 in/in	restricted
Linear Mold Shrinkage, Flow	0.0030 cm/cm	0.0030 in/in	ISO 2577
	0.0033 cm/cm	0.0033 in/in	TM=320°C, TW=100°C
Linear Mold Shrinkage, Transverse	0.010 cm/cm	0.010 in/in	ISO 2577

Mechanical Properties	Metric	English	Comments
Tensile Strength, Yield	200 MPa	29000 psi	50 mm/min; ISO 527-1/-2
Tensile Creep Modulus, 1000 hours	8700 MPa @Strain <=0.500 %	1.26e+6 psi @Strain <=0.500 %	ISO 899-1

Thermal Properties	Metric	English	Comments
Thermal Conductivity	0.280 W/m-K	1.94 BTU-in/hr-ft ² -°F	DIN 52612
Melting Point	295 °C	563 °F	DIN 53765
Maximum Service Temperature, Air	135 °C	275 °F	for 50% loss of tensile strength after 20000hr
	160 °C	320 °F	for 50% loss of tensile strength after 5000hr
	270 °C	518 °F	

Decomposition Temperature Thermal Properties	≥ 350 °C Metric	≥ 662 °F English	Comments
Electrical Properties	Metric	English	Comments
Volume Resistivity	1.00e+12 ohm-cm	1.00e+12 ohm-cm	IEC 60093
Surface Resistance	1.00e+12 ohm	1.00e+12 ohm	IEC 60093
Dielectric Constant	4.4	4.4	IEC 60250
	@Frequency 1.00 Hz	@Frequency 1.00 Hz	
Dissipation Factor	0.030	0.030	IEC 60250
	@Frequency 1.00e+6 Hz	@Frequency 1.00e+6 Hz	
Comparative Tracking Index	600 V	600 V	Test solution A; IEC 60112

Processing Properties	Metric	English	Comments
Zone 1	300 °C	572 °F	Feed Zone
Zone 2	310 °C	590 °F	Compression
Zone 3	320 °C	608 °F	Metering-zone
Zone 4	320 °C	608 °F	Nozzle
Melt Temperature	310 - 330 °C	590 - 626 °F	Injection-molding/Extrusion
	320 °C	608 °F	Optimal
Mold Temperature	80.0 - 120 °C	176 - 248 °F	Injection-molding
	100 °C	212 °F	Optimal
Drying Temperature	110 °C	230 °F	
Dry Time	8 hour	8 hour	
Moisture Content	≤ 0.030 %	≤ 0.030 %	Optimal
	≤ 0.15 %	≤ 0.15 %	

Descriptive Properties	Value	Comments
Color	BK 00564	
Commercial Status	Europe	
Ignition Temperature	>470 °C	ASTM D1929

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China