

## BCC Products BC 8870 Polyurethane Elastomer

Category : Polymer , Thermoset , Polyurethane, TS , Thermoset Polyurethane, Elastomer, Unreinforced , Rubber or Thermoset Elastomer (TSE)

### Material Notes:

BC8870 is a low viscosity two-component urethane casting compound that is specifically formulated for high abrasion and impact resistance. It is recommended for use for the production casting of highly wear-resistant parts and linings. This product is a safe, easy-to-handle, room temperature mixing and curing system that does not contain TDI, MDI, or MOCA. BC8870 is relatively insensitive to typical environmental moisture and will make good void-free parts without the problems that some conventional urethane systems exhibit. Information provided by BCC Products, Inc.

Order this product through the following link:

[http://www.lookpolymers.com/polymer\\_BCC-Products-BC-8870-Polyurethane-Elastomer.php](http://www.lookpolymers.com/polymer_BCC-Products-BC-8870-Polyurethane-Elastomer.php)

Physical Properties	Metric	English	Comments
Specific Gravity	1.10 g/cc	1.10 g/cc	
Brookfield Viscosity	1800 - 2000 cP	1800 - 2000 cP	1.5 min mixed
Linear Mold Shrinkage	0.0025 cm/cm	0.0025 in/in	

Mechanical Properties	Metric	English	Comments
Hardness, Shore D	68 - 72	68 - 72	
Tensile Strength, Ultimate	26.2 MPa	3800 psi	ASTM D412
Elongation at Break	400 %	400 %	
Tensile Modulus	0.248 GPa	36.0 ksi	
Flexural Strength	25.5 MPa	3700 psi	ASTM D790
Flexural Modulus	0.538 GPa	78.0 ksi	ASTM D790
Compressive Strength	67.6 MPa	9800 psi	
Rebound	48 %	48 %	Bayshore; ASTM D575
Tear Strength	114 kN/m	650 pli	ASTM D412
Compression Set	42 %	42 %	method B; ASTM D395

Processing Properties	Metric	English	Comments
Cure Time	4320 - 7200 min	72.0 - 120 hour	full cure
	120 - 180 min	2.00 - 3.00 hour	demold time
	@Temperature 24.0 °C	@Temperature 75.2 °F	

Processing Properties	18 - 20 min Metric	18 - 20 min English	Comments
	@Temperature 24.0 °C	@Temperature 75.2 °F	

Descriptive Properties	Value	Comments
Mix Ratio	100:60 by weight (Part A/Part B)	

## Contact Songhan Plastic Technology Co.,Ltd.

Website : [www.lookpolymers.com](http://www.lookpolymers.com)

Email : [sales@lookpolymers.com](mailto:sales@lookpolymers.com)

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China