

BCC Products MB 1300 Polyurethane Foam Modeling Board

Category: Polymer, Thermoplastic, Polyurethane, TP

Material Notes:

MB 1300 is a Mahogany colored rigid closed-cell polyurethane foam tooling and modeling board. MB 1300 is medium low density foam of approximately 30lbs/ft3 board. Easily cut using CNC machining equipment the MB 1300 is perfectly suited for visual master models, architectural design models as well as design verification and prototype tools. Features: easily machined or hand carved, very little abrasion, no shrinkage, excellent at high speed cutting, excellent surface finish, and exceptional dimensional stability. Uses: proofing intricate CNC designs, numerous tooling aids, temporary master models (automotive/aerospace), various prototypes, architectural models, foundry applications, bases for die models. Information provided by BCC Products, Inc.

Order this product through the following link:

http://www.lookpolymers.com/polymer_BCC-Products-MB-1300-Polyurethane-Foam-Modeling-Board.php

| Physical Properties | Metric | English | Comments |
|---------------------|------------|------------|----------|
| Specific Gravity | 0.497 g/cc | 0.497 g/cc | |

| Mechanical Properties | Metric | English | Comments |
|----------------------------|----------|----------|----------|
| Hardness, Shore D | 58 | 58 | |
| Tensile Strength, Ultimate | 8.62 MPa | 1250 psi | |
| Flexural Strength | 16.5 MPa | 2400 psi | |
| Compressive Strength | 15.2 MPa | 2200 psi | |

| Thermal Properties | Metric | English | Comments |
|----------------------------------|--------------|----------------|----------|
| CTE, linear | 59.4 μm/m-°C | 33.0 µin/in-°F | |
| Maximum Service Temperature, Air | 90.6 °C | 195 °F | |
| Minimum Service Temperature, Air | -184 °C | -300 °F | |

Contact Songhan Plastic Technology Co.,Ltd.

Website: www.lookpolymers.com Email: sales@lookpolymers.com

Tel: +86 021-51131842 Mobile: +86 13061808058

Skype: lookpolymers

Address: United North Road 215, Fengxian District, Shanghai City, China