

## BLUESTAR 201G20 PBT, 20% Glass Filled

Category : Polymer , Thermoplastic , Polyester, TP , Polybutylene Terephthalate (PBT) , Polybutylene Terephthalate (PBT), 20% Glass Fiber Filled

### Material Notes:

Typical Applications: Energy saving lighting Information provided by Polymer Technology and Services, LLC (PTS).

Order this product through the following link:

[http://www.lookpolymers.com/polymer\\_BLUESTAR-201G20-PBT-20-Glass-Filled.php](http://www.lookpolymers.com/polymer_BLUESTAR-201G20-PBT-20-Glass-Filled.php)

Physical Properties	Metric	English	Comments
Specific Gravity	1.54 g/cc	1.54 g/cc	ASTM D792
Moisture Absorption at Equilibrium	0.17 %	0.17 %	50% RH; ASTM D570
Linear Mold Shrinkage, Flow	0.0040 cm/cm	0.0040 in/in	ASTM D955
Linear Mold Shrinkage, Transverse	0.0080 cm/cm	0.0080 in/in	ASTM D955
Melt Flow	38 g/10 min @Load 2.16 kg, Temperature 250 °C	38 g/10 min @Load 4.76 lb, Temperature 482 °F	ASTM D1238

Mechanical Properties	Metric	English	Comments
Tensile Strength at Break	105 MPa	15200 psi	ASTM D638
Flexural Strength	170 MPa	24700 psi	ASTM D790
Flexural Modulus	7.00 GPa	1020 ksi	ASTM D790
Izod Impact, Notched (ISO)	8.00 kJ/m <sup>2</sup>	3.81 ft-lb/in <sup>2</sup>	ASTM D256
Izod Impact, Unnotched (ISO)	50.0 kJ/m <sup>2</sup>	23.8 ft-lb/in <sup>2</sup>	ASTM D256

Thermal Properties	Metric	English	Comments
Deflection Temperature at 0.46 MPa (66 psi)	215 °C	419 °F	ASTM D648
Deflection Temperature at 1.8 MPa (264 psi)	198 °C	388 °F	ASTM D648
Flammability, UL94	V-0	V-0	
	@Thickness 0.800 mm	@Thickness 0.0315 in	
	V-0	V-0	
	@Thickness 1.60 mm	@Thickness 0.0630 in	
	V-0	V-0	
	@Thickness 3.20 mm	@Thickness 0.126 in	

Thermal Properties

Metric

English

Comments

## Contact Songhan Plastic Technology Co.,Ltd.

Website : [www.lookpolymers.com](http://www.lookpolymers.com)

Email : [sales@lookpolymers.com](mailto:sales@lookpolymers.com)

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China