

## BLUESTAR LXS 115 PPE-PS

Category : Polymer , Thermoplastic , Polyphenylene Ether/PPO , Polystyrene (PS) , Polystyrene + Polyphenylene Ether, Unreinforced

### Material Notes:

Typical Applications: Auto connect parts  
Fire Rated  
Information provided by Polymer Technology and Services, LLC (PTS).

Order this product through the following link:

[http://www.lookpolymers.com/polymer\\_BLUESTAR-LXS-115-PPE-PS.php](http://www.lookpolymers.com/polymer_BLUESTAR-LXS-115-PPE-PS.php)

Physical Properties	Metric	English	Comments
Specific Gravity	1.07 g/cc	1.07 g/cc	ASTM D792
Water Absorption	0.10 %	0.10 %	ASTM D570
	@Temperature 23.0 °C, Time 86400 sec	@Temperature 73.4 °F, Time 24.0 hour	
Linear Mold Shrinkage, Flow	0.0050 - 0.0070 cm/cm	0.0050 - 0.0070 in/in	ASTM D955
Melt Flow	15 g/10 min	15 g/10 min	ASTM D1238
	@Load 5.00 kg, Temperature 300 °C	@Load 11.0 lb, Temperature 572 °F	

Mechanical Properties	Metric	English	Comments
Tensile Strength at Break	65.0 MPa	9430 psi	type I; ASTM D638
Elongation at Break	28 %	28 %	type I; ASTM D638
Flexural Strength	92.0 MPa	13300 psi	2.6 mm/min; ASTM D790
Flexural Modulus	2.40 GPa	348 ksi	2.6 mm/min; ASTM D790
Izod Impact, Notched (ISO)	15.0 kJ/m <sup>2</sup>	7.14 ft-lb/in <sup>2</sup>	ASTM D256

Thermal Properties	Metric	English	Comments
Deflection Temperature at 1.8 MPa (264 psi)	150 °C	302 °F	ASTM D648
	@Thickness 6.40 mm	@Thickness 0.252 in	
Flammability, UL94	V-0	V-0	
	@Thickness 3.20 mm	@Thickness 0.126 in	
	V-0	V-0	
	@Thickness 1.60 mm	@Thickness 0.0630 in	
	V-0	V-0	
	@Thickness 0.800 mm	@Thickness 0.0315 in	

## **Contact Songhan Plastic Technology Co.,Ltd.**

**Website : [www.lookpolymers.com](http://www.lookpolymers.com)**

**Email : [sales@lookpolymers.com](mailto:sales@lookpolymers.com)**

**Tel : +86 021-51131842**

**Mobile : +86 13061808058**

**Skype : lookpolymers**

**Address : United North Road 215,Fengxian District, Shanghai City,China**