

BLUESTAR LXS 314 G10 PPE-HIPS, 10% Glass Filled

Category : Polymer , Thermoplastic , Polyphenylene Ether/PPO , Polystyrene (PS) , Polystyrene + Polyphenylene Ether, Glass Filler

Material Notes:Typical Applications: Water industrial parts
Information provided by Polymer Technology and Services, LLC (PTS).

Order this product through the following link:

http://www.lookpolymers.com/polymer_BLUESTAR-LXS-314-G10-PPE-HIPS-10-Glass-Filled.php

Physical Properties	Metric	English	Comments
Specific Gravity	1.15 g/cc	1.15 g/cc	ASTM D792
Water Absorption	0.10 %	0.10 %	ASTM D570
	@Temperature 23.0 °C, Time 86400 sec	@Temperature 73.4 °F, Time 24.0 hour	
Linear Mold Shrinkage, Flow	0.0030 - 0.0050 cm/cm	0.0030 - 0.0050 in/in	ASTM D955
Melt Flow	21 g/10 min	21 g/10 min	ASTM D1238
	@Load 5.00 kg, Temperature 300 °C	@Load 11.0 lb, Temperature 572 °F	

Mechanical Properties	Metric	English	Comments
Tensile Strength at Break	60.0 MPa	8700 psi	type I; ASTM D638
Elongation at Break	10 %	10 %	type I; ASTM D638
Flexural Strength	110 MPa	16000 psi	2.6 mm/min; ASTM D790
Flexural Modulus	3.20 GPa	464 ksi	2.6 mm/min; ASTM D790
Izod Impact, Notched (ISO)	14.0 kJ/m ²	6.66 ft-lb/in ²	ASTM D256

Thermal Properties	Metric	English	Comments
Deflection Temperature at 1.8 MPa (264 psi)	120 °C	248 °F	ASTM D648
	@Thickness 6.40 mm	@Thickness 0.252 in	

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China