

BNZ Materials PA 23 Insulating Firebrick

Category : Ceramic , Oxide , Silicon Oxide

Material Notes:

BNZ produces many types of Insulating Fire Brick (IFB) for use in applications from 2,000°F (1,093°C) to 3,200°F (1,760°C). Each type is formulated to meet specific thermal and physical requirements and after firing is machined to precise tolerances. Made from high purity refractory clays and other ceramic raw materials, these IFB contain a carefully graded organic filler which is burned out during manufacture to give a uniform controlled pore structure. Information provided by BNZ Materials Inc.

Order this product through the following link:

http://www.lookpolymers.com/polymer_BNZ-Materials-PA-23-Insulating-Firebrick.php

Physical Properties	Metric	English	Comments
Density	0.705 g/cc	0.0255 lb/in ³	ASTM C134
Deformation	-0.500 % @Temperature 1093 °C, Time 5400 sec	-0.500 % @Temperature 1999 °F, Time 1.50 hour	10 psi load, Hot Load Strength; ASTM C16

Mechanical Properties	Metric	English	Comments
Modulus of Rupture	0.000790 GPa	0.115 ksi	
Compressive Strength	0.981 MPa	142 psi	Cold Crush Strength

Thermal Properties	Metric	English	Comments
CTE, linear	5.60 μm/m-°C @Temperature 20.0 - 1093 °C	3.11 μin/in-°F @Temperature 68.0 - 1999 °F	
Thermal Conductivity	0.230 W/m-K @Temperature 260 °C	1.60 BTU-in/hr-ft ² -°F @Temperature 500 °F	ASTM C182
	0.290 W/m-K @Temperature 538 °C	2.01 BTU-in/hr-ft ² -°F @Temperature 1000 °F	ASTM C182
	0.350 W/m-K @Temperature 816 °C	2.43 BTU-in/hr-ft ² -°F @Temperature 1500 °F	ASTM C182
	0.370 W/m-K @Temperature 1093 °C	2.57 BTU-in/hr-ft ² -°F @Temperature 1999 °F	ASTM C182
Maximum Service Temperature, Air	1260 °C	2300 °F	
	0.00 %	0.00 %	Permanent Linear Change; ASTM

Shrinkage Thermal Properties	@Temperature 1232 °C, Metric Time 66400 sec	@Temperature 2250 °F, English Time 24.0 hour	C210 Comments
---------------------------------	---	--	------------------

Component Elements Properties	Metric	English	Comments
Al2O3	42.5 %	42.5 %	
CaO	2.5 %	2.5 %	
Fe2O3	0.70 %	0.70 %	
MgO	0.10 %	0.10 %	
Na2O	0.40 %	0.40 %	Includes K ₂ O
SiO2	51.5 %	51.5 %	
TiO2	1.5 %	1.5 %	

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China