

Bales Mold Service AMS-2404-C, AMS-2405-B Mold Coating

Category : Metal , Other Engineering Material , Ceramic/Metallic Coating

Material Notes:

Description: Bales's application of .0002-.0003 Electroless Nickel with 10.5% to 12% phosphorus offers excellent corrosion protection against P.V.C. and other corrosive materials. Cores, cavities and entire mold bases can be coated with this engineering grade Electroless Nickel, offering a more uniform plated deposit than chrome. Information provided by Bales Mold Service Inc.

Order this product through the following link:

http://www.lookpolymers.com/polymer_Bales-Mold-Service-AMS-2404-C-AMS-2405-B-Mold-Coating.php

Mechanical Properties	Metric	English	Comments
Hardness, Rockwell C	50	50	
Coefficient of Friction	<= 0.45	<= 0.45	

Processing Properties	Metric	English	Comments
Processing Temperature	85.0 °C	185 °F	Applied Temperature

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China