

Bales Mold Service Nicklon® Nickel-P.T.F.E. Mold Coating

Category : Metal , Metal Matrix Composite , Nonferrous Metal , Nickel Alloy , Other Engineering Material , Ceramic/Metallic Coating

Material Notes:

Autocatalytic application provides a uniform layer of 22%-24% PTFE over the deepest ribs and most complex details. It is also corrosion resistant. Excellent Release Properties for: Deep Ribs "No Draft" Cores Textured Surfaces Difficult to Eject Polymers Information provided by Bales Mold Service Inc.

Order this product through the following link:

http://www.lookpolymers.com/polymer_Bales-Mold-Service-Nicklon-Nickel-PTFE-Mold-Coating.php

Mechanical Properties	Metric	English	Comments
Hardness, Rockwell C	45	45	
Coefficient of Friction	<= 0.10	<= 0.10	

Processing Properties	Metric	English	Comments
Processing Temperature	85.0 °C	185 °F	Applied Temperature

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215, Fengxian District, Shanghai City, China