

Bales Mold Service QQ-N-290 Sulfamate Nickel Mold Coating

Category : Metal , Nonferrous Metal , Nickel Alloy , Other Engineering Material , Ceramic/Metallic Coating

Material Notes:

Selective plating for dimensional correction is a typical application for Sulfamate Nickel because of it's ability to deposit up to .250 with less inclusions and porosity than most electrolytic deposits. This is an excellent choice for deposits in excess of .015-.020 thick. Information provided by Bales Molding Service Inc.

Order this product through the following link:

http://www.lookpolymers.com/polymer_Bales-Mold-Service-QQ-N-290-Sulfamate-Nickel-Mold-Coating.php

Mechanical Properties	Metric	English	Comments
Hardness, Rockwell C	40	40	
Coefficient of Friction	<= 0.45	<= 0.45	

Processing Properties	Metric	English	Comments
Processing Temperature	60.0 °C	140 °F	Applied Temperature

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China