

Bapolene® 142B Polyethylene Film Grade

Category : Polymer , Thermoplastic , Polyethylene (PE) , LLDPE

Material Notes:

Bapolene 142B is a hexene linear low density polyethylene for blown film applications requiring superior impact strength. Product is designed to exhibit performance similar to that of super hexene products. It complies with US FDA 21CFR177.1520. Applications: General purpose, trash bags, and liners. Bapolene® and Bapolan® are registered trademarks of Bamberger Polymers, Inc. Information provided by Bamberger Polymers

Order this product through the following link:

http://www.lookpolymers.com/polymer_Bapolene-142B-Polyethylene-Film-Grade.php

Physical Properties	Metric	English	Comments
Density	0.917 g/cc	0.0331 lb/in ³	ASTM D-1505
Thickness	25.4 microns	1.00 mil	2.5:1 BUR as tested
Melt Flow	1.0 g/10 min @Load 2.16 kg, Temperature 190 °C	1.0 g/10 min @Load 4.76 lb, Temperature 374 °F	ASTM D1238

Mechanical Properties	Metric	English	Comments
Film Elongation at Break, MD	500 %	500 %	ASTM D-882
Film Elongation at Break, TD	650 %	650 %	ASTM D-882
Elmendorf Tear Strength MD	375 g	375 g	ASTM D-1922
Elmendorf Tear Strength TD	600 g	600 g	ASTM D-1922
Elmendorf Tear Strength, MD	14.8 g/micron	375 g/mil	ASTM D-1922
Elmendorf Tear Strength, TD	23.6 g/micron	600 g/mil	ASTM D-1922
Dart Drop Test	400 g	0.882 lb	F _{>50} ; ASTM D-1709
Film Tensile Strength at Break, MD	37.0 MPa	5370 psi	ASTM D-882
Film Tensile Strength at Break, TD	27.0 MPa	3920 psi	ASTM D-882

Descriptive Properties	Value	Comments
Process	Blown Film	
	Film	
Region	Europe/Turkey	Bamberger Polymers Distribution
	International	Bamberger Polymers Distribution

Descriptive Properties	Value	Comments
	Mexico	Bamberger Polymers Distribution
	US & Canada	Bamberger Polymers Distribution

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China