

## Barlog Plastics KEBAFLEX SG 65 A.01 TPE-S, Shore A65, natural

Category : Polymer , Thermoplastic , Elastomer, TPE , Styrenic TPE

**Material Notes:**

TPE-S information provided by BARLOG plastics GmbH.

Order this product through the following link:

[http://www.lookpolymers.com/polymer\\_Barlog-Plastics-KEBAFLEX-SG-65-A01-TPE-S-Shore-A65-natural.php](http://www.lookpolymers.com/polymer_Barlog-Plastics-KEBAFLEX-SG-65-A01-TPE-S-Shore-A65-natural.php)

Physical Properties	Metric	English	Comments
Density	1.19 g/cc	0.0430 lb/in <sup>3</sup>	ISO 1183
Linear Mold Shrinkage, Flow	0.024 cm/cm	0.024 in/in	ISO 294-4
Linear Mold Shrinkage, Transverse	0.0060 cm/cm	0.0060 in/in	ISO 294-4

Mechanical Properties	Metric	English	Comments
Hardness, Shore A	65	65	
Tensile Strength at Break	7.00 MPa	1020 psi	ISO 527-1
Elongation at Break	660 %	660 %	ISO 527-1

Descriptive Properties	Value	Comments
Resin Type	TPE-S	

## Contact Songhan Plastic Technology Co.,Ltd.

Website : [www.lookpolymers.com](http://www.lookpolymers.com)

Email : [sales@lookpolymers.com](mailto:sales@lookpolymers.com)

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215, Fengxian District, Shanghai City, China