

## Barlog Plastics KEBAFORM C 274 VT POM Copolymer unreinforced, antistatic

Category : Polymer , Thermoplastic , Acetal (POM) , Acetal Copolymer, Unreinforced

### Material Notes:

POM Information provided by BARLOG plastics GmbH.

Order this product through the following link:

[http://www.lookpolymers.com/polymer\\_Barlog-Plastics-KEBAFORM-C-274-VT-POM-Copolymer-unreinforced-antistatic.php](http://www.lookpolymers.com/polymer_Barlog-Plastics-KEBAFORM-C-274-VT-POM-Copolymer-unreinforced-antistatic.php)

Physical Properties	Metric	English	Comments
Density	1.41 g/cc	0.0509 lb/in <sup>3</sup>	ISO 1183
Moisture Absorption at Equilibrium	0.20 %	0.20 %	similar to ISO 62 test
Linear Mold Shrinkage, Flow	0.020 cm/cm	0.020 in/in	ISO 294-4
Linear Mold Shrinkage, Transverse	0.020 cm/cm	0.020 in/in	ISO 294-4
Melt Flow	27 g/10 min @Load 2.16 kg, Temperature 190 °C	27 g/10 min @Load 4.76 lb, Temperature 374 °F	ISO 1133

Mechanical Properties	Metric	English	Comments
Tensile Strength, Yield	65.0 MPa	9430 psi	ISO 527-1
Elongation at Yield	9.0 %	9.0 %	ISO 527-1
Tensile Modulus	2.80 GPa	406 ksi	ISO 527-1
Charpy Impact, Notched	0.550 J/cm <sup>2</sup>	2.62 ft-lb/in <sup>2</sup>	ISO 179-1eA

Thermal Properties	Metric	English	Comments
Melting Point	166 °C	331 °F	10°C/min; ISO 11357-1/-3
Deflection Temperature at 1.8 MPa (264 psi)	110 °C	230 °F	ISO 75-1/-2

Electrical Properties	Metric	English	Comments
Volume Resistivity	2.00e+15 ohm-cm	2.00e+15 ohm-cm	IEC 60093
Surface Resistance	1.00e+13 ohm	1.00e+13 ohm	IEC 60093

Descriptive Properties	Value	Comments
Resin Type	POM	

## **Contact Songhan Plastic Technology Co.,Ltd.**

**Website : [www.lookpolymers.com](http://www.lookpolymers.com)**

**Email : [sales@lookpolymers.com](mailto:sales@lookpolymers.com)**

**Tel : +86 021-51131842**

**Mobile : +86 13061808058**

**Skype : lookpolymers**

**Address : United North Road 215,Fengxian District, Shanghai City,China**