

## Barlog Plastics KEBAFORM C 50.0 POM Copolymer unreinforced

Category : Polymer , Thermoplastic , Acetal (POM) , Acetal Copolymer, Unreinforced

### Material Notes:

POM Information provided by BARLOG plastics GmbH.

Order this product through the following link:

[http://www.lookpolymers.com/polymer\\_Barlog-Plastics-KEBAFORM-C-500-POM-Copolymer-unreinforced.php](http://www.lookpolymers.com/polymer_Barlog-Plastics-KEBAFORM-C-500-POM-Copolymer-unreinforced.php)

Physical Properties	Metric	English	Comments
Density	1.41 g/cc	0.0509 lb/in <sup>3</sup>	ISO 1183
Linear Mold Shrinkage, Flow	0.020 cm/cm	0.020 in/in	ISO 294-4
Linear Mold Shrinkage, Transverse	0.020 cm/cm	0.020 in/in	ISO 294-4
Melt Flow	5.0 g/10 min @Load 2.16 kg, Temperature 190 °C	5.0 g/10 min @Load 4.76 lb, Temperature 374 °F	ISO 1133

Mechanical Properties	Metric	English	Comments
Tensile Strength, Yield	62.0 MPa	8990 psi	ISO 527-1
Elongation at Yield	11 %	11 %	ISO 527-1
Tensile Modulus	2.50 GPa	363 ksi	ISO 527-1
Charpy Impact Unnotched	NB	NB	ISO 179-1eU
Charpy Impact, Notched	0.800 J/cm <sup>2</sup>	3.81 ft-lb/in <sup>2</sup>	ISO 179-1eA

Thermal Properties	Metric	English	Comments
Melting Point	166 °C	331 °F	10°C/min; ISO 11357-1/-3
Deflection Temperature at 1.8 MPa (264 psi)	110 °C	230 °F	ISO 75-1/-2
Flammability, UL94	HB	HB	IEC 60695-11-10

Electrical Properties	Metric	English	Comments
Volume Resistivity	1.00e+16 ohm-cm	1.00e+16 ohm-cm	IEC 60093
Surface Resistance	1.00e+16 ohm	1.00e+16 ohm	IEC 60093

Descriptive Properties	Value	Comments
Resin Type	POM	

Descriptive Properties	Value	Comments
------------------------	-------	----------

## Contact Songhan Plastic Technology Co.,Ltd.

Website : [www.lookpolymers.com](http://www.lookpolymers.com)

Email : [sales@lookpolymers.com](mailto:sales@lookpolymers.com)

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China