

Barlog Plastics KEBATER BFA15 PBT, 15% glass fiber reinforced, flame retardant

Category : Polymer , Thermoplastic , Polyester, TP , Polybutylene Terephthalate (PBT) , Polybutylene Terephthalate (PBT), Glass Fiber Filled, Flame Retardant

Material Notes:

PBT-GF15 FR Information provided by BARLOG plastics GmbH.

Order this product through the following link:

http://www.lookpolymers.com/polymer_Barlog-Plastics-KEBATER-BFA15-PBT-15-glass-fiber-reinforced-flame-retardant.php

Physical Properties	Metric	English	Comments
Density	1.50 g/cc	0.0542 lb/in ³	ISO 1183
Moisture Absorption at Equilibrium	0.20 %	0.20 %	similar to ISO 62 test

Mechanical Properties	Metric	English	Comments
Tensile Strength at Break	85.0 MPa	12300 psi	ISO 527-1
Elongation at Break	4.5 %	4.5 %	ISO 527-1
Tensile Modulus	6.60 GPa	957 ksi	ISO 527-1
Charpy Impact Unnotched	4.50 J/cm ²	21.4 ft-lb/in ²	ISO 179-1eU
Charpy Impact, Notched	0.750 J/cm ²	3.57 ft-lb/in ²	ISO 179-1eA

Thermal Properties	Metric	English	Comments
CTE, linear, Parallel to Flow	55.0 µm/m-°C	30.6 µin/in-°F	ISO 11359-1/-2
Melting Point	225 °C	437 °F	10°C/min; ISO 11357-1/-3
Deflection Temperature at 0.46 MPa (66 psi)	220 °C	428 °F	ISO 75-1/-2
Deflection Temperature at 1.8 MPa (264 psi)	205 °C	401 °F	ISO 75-1/-2
Flammability, UL94	V-0 @Thickness 0.800 mm	V-0 @Thickness 0.0315 in	UL Registered; IEC 60695-11-10

Electrical Properties	Metric	English	Comments
Volume Resistivity	1.00e+17 ohm-cm	1.00e+17 ohm-cm	IEC 60093
Surface Resistance	1.00e+13 ohm	1.00e+13 ohm	IEC 60093

Descriptive Properties	Value	Comments
Resin Type	PBT-GF15 FR	

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China