

Barlog Plastics KEBATER BFA30 PBT, 30% glass fiber reinforced, flame retardant

Category : Polymer , Thermoplastic , Polyester, TP , Polybutylene Terephthalate (PBT) , Polybutylene Terephthalate (PBT), Glass Fiber Filled, Flame Retardant

Material Notes:

PBT-GF30 FR Information provided by BARLOG plastics GmbH.

Order this product through the following link:

http://www.lookpolymers.com/polymer_Barlog-Plastics-KEBATER-BFA30-PBT-30-glass-fiber-reinforced-flame-retardant.php

Physical Properties	Metric	English	Comments
Density	1.65 g/cc	0.0596 lb/in ³	ISO 1183
Moisture Absorption at Equilibrium	0.15 %	0.15 %	similar to ISO 62 test

Mechanical Properties	Metric	English	Comments
Tensile Strength at Break	130 MPa	18900 psi	ISO 527-1
Elongation at Break	3.0 %	3.0 %	ISO 527-1
Tensile Modulus	10.5 GPa	1520 ksi	ISO 527-1
Charpy Impact Unnotched	5.00 J/cm ²	23.8 ft-lb/in ²	ISO 179-1eU
Charpy Impact, Notched	1.05 J/cm ²	5.00 ft-lb/in ²	ISO 179-1eA

Thermal Properties	Metric	English	Comments
CTE, linear, Parallel to Flow	40.0 µm/m-°C	22.2 µin/in-°F	ISO 11359-1/-2
Melting Point	225 °C	437 °F	10°C/min; ISO 11357-1/-3
Deflection Temperature at 0.46 MPa (66 psi)	220 °C	428 °F	ISO 75-1/-2
Deflection Temperature at 1.8 MPa (264 psi)	208 °C	406 °F	ISO 75-1/-2
Flammability, UL94	V-0 @Thickness 0.800 mm	V-0 @Thickness 0.0315 in	UL Registered; IEC 60695-11-10

Electrical Properties	Metric	English	Comments
Volume Resistivity	1.00e+17 ohm-cm	1.00e+17 ohm-cm	IEC 60093
Surface Resistance	1.00e+13 ohm	1.00e+13 ohm	IEC 60093

Descriptive Properties	Value	Comments
Resin Type	PBT-GF30 FR	

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China