

Beijing Chemical Industry KAIFA® 201-G20R PBT Resin

Category : Polymer , Thermoplastic , Polyester, TP , Polybutylene Terephthalate (PBT) , Polybutylene Terephthalate (PBT), 20% Glass Fiber Filled

Material Notes:

15% glass fiber reinforced, good flow and toughness Information provided by Beijing Chemical Industry Research Institute (Group)

Order this product through the following link:

http://www.lookpolymers.com/polymer_Beijing-Chemical-Industry-KAIFA-201-G20R-PBT-Resin.php

Physical Properties	Metric	English	Comments
Density	1.35 g/cc	0.0488 lb/in ³	ASTM D792
Water Absorption	0.050 %	0.050 %	24 hr; ASTM D570
Linear Mold Shrinkage	0.0080 - 0.010 cm/cm	0.0080 - 0.010 in/in	ASTM D955

Mechanical Properties	Metric	English	Comments
Tensile Strength at Break	115 MPa	16700 psi	ASTM D638
Elongation at Break	10 %	10 %	ASTM D638
Flexural Strength	175 MPa	25400 psi	ASTM D790
Flexural Modulus	5.50 GPa	798 ksi	ASTM D790
Charpy Impact Unnotched	6.00 J/cm ²	28.6 ft-lb/in ²	ISO179
Charpy Impact, Notched	1.80 J/cm ²	8.57 ft-lb/in ²	ISO179

Thermal Properties	Metric	English	Comments
CTE, linear	55.0 μm/m-°C	30.6 μin/in-°F	ASTM D696
	@Temperature -30.0 - 30.0 °C	@Temperature -22.0 - 86.0 °F	
Deflection Temperature at 0.46 MPa (66 psi)	220 °C	428 °F	ASTM D648
Deflection Temperature at 1.8 MPa (264 psi)	200 °C	392 °F	ASTM D648
Flammability, UL94	HB	HB	
	@Thickness 3.20 mm	@Thickness 0.126 in	

Electrical Properties	Metric	English	Comments
Volume Resistivity	1.00e+16 ohm-cm	1.00e+16 ohm-cm	ASTM D257
	3.2	3.2	

Dielectric Constant Electrical Properties	Metric @Frequency 1e+6 Hz	English @Frequency 1e+6 Hz	ASTM D150 Comments
Dielectric Strength	23.0 kV/mm @Thickness 2.00 mm	584 kV/in @Thickness 0.0787 in	ASTM D149
Dissipation Factor	0.018 @Frequency 1e+6 Hz	0.018 @Frequency 1e+6 Hz	ASTM D150
Comparative Tracking Index	600 V @Thickness 3.20 mm	600 V @Thickness 0.126 in	ASTM D3638

Processing Properties	Metric	English	Comments
Middle Barrel Temperature	225 - 255 °C	437 - 491 °F	
Nozzle Temperature	245 °C	473 °F	
Mold Temperature	40.0 - 80.0 °C	104 - 176 °F	
Drying Temperature	130 °C	266 °F	
Dry Time	4 hour	4 hour	
Injection Pressure	80.0 - 120 MPa	11600 - 17400 psi	
Back Pressure	8.00 - 18.0 MPa	1160 - 2610 psi	
Screw Speed	<= 100 rpm	<= 100 rpm	

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China