

## Beijing Chemical Industry KAIFA® GL3300 ABS Flame-Retardant Grade

Category : Polymer , Thermoplastic , ABS Polymer , Acrylonitrile Butadiene Styrene (ABS), Unreinforced, Flame Retardant

### Material Notes:

Good flammability Information provided by Beijing Chemical Industry Research Institute (Group)

Order this product through the following link:

[http://www.lookpolymers.com/polymer\\_Beijing-Chemical-Industry-KAIFA-GL3300-ABS-Flame-Retardant-Grade.php](http://www.lookpolymers.com/polymer_Beijing-Chemical-Industry-KAIFA-GL3300-ABS-Flame-Retardant-Grade.php)

Physical Properties	Metric	English	Comments
Density	1.20 g/cc	0.0434 lb/in <sup>3</sup>	ASTM D792
Water Absorption	0.30 %	0.30 %	24 hr; ASTM D570

Mechanical Properties	Metric	English	Comments
Tensile Strength at Break	37.0 MPa	5370 psi	ASTM D638
Elongation at Break	18 %	18 %	ASTM D638
Flexural Strength	60.0 MPa	8700 psi	ASTM D790
Flexural Modulus	2.00 GPa	290 ksi	ASTM D790
Izod Impact, Notched	0.130 J/cm @Thickness 3.20 mm	0.244 ft-lb/in @Thickness 0.126 in	ASTM D256

Thermal Properties	Metric	English	Comments
Deflection Temperature at 1.8 MPa (264 psi)	82.0 °C	180 °F	ASTM D648
Flammability, UL94	V-0 @Thickness 1.60 mm	V-0 @Thickness 0.0630 in	
	V-0 @Thickness 3.20 mm	V-0 @Thickness 0.126 in	

Electrical Properties	Metric	English	Comments
Volume Resistivity	1.00e+15 ohm-cm	1.00e+15 ohm-cm	ASTM D257

Processing Properties	Metric	English	Comments
Processing Temperature	180 - 230 °C	356 - 446 °F	Resin Temp.
Rear Barrel Temperature	190 °C	374 °F	
Middle Barrel Temperature			

Processing Properties	210 °C Metric	410 °F English	Comments
Front Barrel Temperature	220 °C	428 °F	
Nozzle Temperature	215 °C	419 °F	
Mold Temperature	60.0 - 80.0 °C	140 - 176 °F	
Drying Temperature	80.0 - 90.0 °C @Thickness 30.0 mm	176 - 194 °F @Thickness 1.18 in	
Dry Time	4 hour @Thickness 30.0 mm	4 hour @Thickness 1.18 in	
Injection Pressure	80.0 - 130 MPa	11600 - 18900 psi	injection speed: 80 - 120 rpm
Back Pressure	1.00 - 2.00 MPa	145 - 290 psi	Mold Pressure
Screw Speed	100 rpm	100 rpm	

## Contact Songhan Plastic Technology Co.,Ltd.

Website : [www.lookpolymers.com](http://www.lookpolymers.com)

Email : [sales@lookpolymers.com](mailto:sales@lookpolymers.com)

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China