

Beijing Chemical Industry KAIFA® MN201-G30 Nylon 66 Resin

Category : Polymer , Thermoplastic , Nylon , Nylon 66 , Nylon 66, 30% Glass Fiber Filled

Material Notes:

30% glass fiber reinforced, thermal resistant Information provided by Beijing Chemical Industry Research Institute (Group)

Order this product through the following link:

http://www.lookpolymers.com/polymer_Beijing-Chemical-Industry-KAIFA-MN201-G30-Nylon-66-Resin.php

Physical Properties	Metric	English	Comments
Density	1.35 g/cc	0.0488 lb/in ³	ASTM D792
Linear Mold Shrinkage	0.0040 - 0.0080 cm/cm	0.0040 - 0.0080 in/in	ASTM D955

Mechanical Properties	Metric	English	Comments
Tensile Strength at Break	150 MPa	21800 psi	ASTM D638
Flexural Strength	210 MPa	30500 psi	ASTM D790
Charpy Impact Unnotched	7.50 J/cm ²	35.7 ft-lb/in ²	ISO179
Charpy Impact, Notched	1.50 J/cm ²	7.14 ft-lb/in ²	ISO179

Thermal Properties	Metric	English	Comments
Deflection Temperature at 1.8 MPa (264 psi)	250 °C	482 °F	ASTM D648
Flammability, UL94	HB @Thickness 3.20 mm	HB @Thickness 0.126 in	

Electrical Properties	Metric	English	Comments
Volume Resistivity	1.00e+15 ohm-cm	1.00e+15 ohm-cm	ASTM D257
Dielectric Constant	3.1 @Frequency 1e+6 Hz	3.1 @Frequency 1e+6 Hz	ASTM D150
Dielectric Strength	30.0 kV/mm @Thickness 2.00 mm	762 kV/in @Thickness 0.0787 in	ASTM D149
Dissipation Factor	0.030 @Frequency 1e+6 Hz	0.030 @Frequency 1e+6 Hz	ASTM D150

Processing Properties	Metric	English	Comments
Rear Barrel Temperature	230 - 240 °C	446 - 464 °F	

Processing Properties	Metric	English	Comments
Mold Barrel Temperature	265 - 270 °C	509 - 518 °F	
Front Barrel Temperature	265 - 270 °C	509 - 518 °F	
Nozzle Temperature	265 - 270 °C	509 - 518 °F	
Mold Temperature	60.0 - 90.0 °C	140 - 194 °F	
Drying Temperature	130 °C	266 °F	
Dry Time	4 hour	4 hour	
Injection Pressure	90.0 - 120 MPa	13100 - 17400 psi	

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China