

## Beijing Chemical Industry KAIFA® MN301-G20 Nylon 66 Resin

Category : Polymer , Thermoplastic , Nylon , Nylon 66 , Nylon 66, Glass Fiber Filled, Flame Retardant

### Material Notes:

20% glass fiber reinforced, flame retardant Information provided by Beijing Chemical Industry Research Institute (Group)

Order this product through the following link:

[http://www.lookpolymers.com/polymer\\_Beijing-Chemical-Industry-KAIFA-MN301-G20-Nylon-66-Resin.php](http://www.lookpolymers.com/polymer_Beijing-Chemical-Industry-KAIFA-MN301-G20-Nylon-66-Resin.php)

Physical Properties	Metric	English	Comments
Density	1.48 g/cc	0.0535 lb/in <sup>3</sup>	ASTM D792
Linear Mold Shrinkage	0.0040 - 0.0080 cm/cm	0.0040 - 0.0080 in/in	ASTM D955

Mechanical Properties	Metric	English	Comments
Tensile Strength at Break	110 MPa	16000 psi	ASTM D638
Flexural Strength	155 MPa	22500 psi	ASTM D790
Charpy Impact Unnotched	5.60 J/cm <sup>2</sup>	26.7 ft-lb/in <sup>2</sup>	ISO179
Charpy Impact, Notched	1.00 J/cm <sup>2</sup>	4.76 ft-lb/in <sup>2</sup>	ISO179

Thermal Properties	Metric	English	Comments
Deflection Temperature at 1.8 MPa (264 psi)	235 °C	455 °F	ASTM D648
Flammability, UL94	V-0 @Thickness 3.20 mm	V-0 @Thickness 0.126 in	

Electrical Properties	Metric	English	Comments
Volume Resistivity	1.00e+16 ohm-cm	1.00e+16 ohm-cm	ASTM D257
Dielectric Constant	3.2 @Frequency 1e+6 Hz	3.2 @Frequency 1e+6 Hz	ASTM D150
Dielectric Strength	28.0 kV/mm @Thickness 2.00 mm	711 kV/in @Thickness 0.0787 in	ASTM D149
Dissipation Factor	0.017 @Frequency 1e+6 Hz	0.017 @Frequency 1e+6 Hz	ASTM D150

Processing Properties	Metric	English	Comments
Rear Barrel Temperature	230 - 240 °C	446 - 464 °F	

Processing Properties	Metric	English	Comments
Mold Barrel Temperature	265 - 270 °C	509 - 518 °F	
Front Barrel Temperature	265 - 270 °C	509 - 518 °F	
Nozzle Temperature	265 - 270 °C	509 - 518 °F	
Mold Temperature	60.0 - 90.0 °C	140 - 194 °F	
Drying Temperature	130 °C	266 °F	
Dry Time	4 hour	4 hour	
Injection Pressure	90.0 - 120 MPa	13100 - 17400 psi	

## Contact Songhan Plastic Technology Co.,Ltd.

Website : [www.lookpolymers.com](http://www.lookpolymers.com)

Email : [sales@lookpolymers.com](mailto:sales@lookpolymers.com)

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China