

Beijing Ranger Chem BLUESTAR® 1084 PBT

Category : Polymer , Thermoplastic , Polyester, TP , Polybutylene Terephthalate (PBT)

Material Notes:

Can be used directly for spinning, and producing color concentrates. It can also be used for production after reinforcement & compounding. Information provided by Beijing Ranger Chemical Co.

Order this product through the following link:

http://www.lookpolymers.com/polymer_Beijing-Ranger-Chem-BLUESTAR-1084-PBT.php

Physical Properties	Metric	English	Comments
Density	1.30 - 1.31 g/cc	0.0470 - 0.0473 lb/in ³	ISO 1183
Viscosity Test	0.82 - 0.86 cm ³ /g	0.82 - 0.86 cm ³ /g	Q/NHS501
Melt Flow	55 - 65 g/10 min	55 - 65 g/10 min	ISO 1133

Mechanical Properties	Metric	English	Comments
Tensile Strength, Yield	50.0 - 60.0 MPa	7250 - 8700 psi	ISO 527

Chemical Properties	Metric	English	Comments
Carboxyl End Groups	0.030 meq/kg	0.030 meq/kg	Q/NHS501

Processing Properties	Metric	English	Comments
Melt Temperature	220 - 225 °C	428 - 437 °F	
Moisture Content	0.30 %	0.30 %	

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China