

Beijing Ranger Chem E-39-D Semi Solid Epoxy Resin

Category : Polymer , Thermoset , Epoxy , Epoxy Cure Resin

Material Notes:

Information provided by Beijing Ranger Chemical Co.

Order this product through the following link:

http://www.lookpolymers.com/polymer_Beijing-Ranger-Chem-E-39-D-Semi-Solid-Epoxy-Resin.php

| Physical Properties | Metric | English | Comments |
|---------------------|----------|----------|----------|
| Volatiles | <= 1.0 % | <= 1.0 % | |

| Thermal Properties | Metric | English | Comments |
|--------------------|----------------|----------------|----------|
| Softening Point | 25.0 - 32.0 °C | 77.0 - 89.6 °F | |

| Descriptive Properties | Value | Comments |
|---------------------------|---------|----------|
| Epoxy Equivalent g/eq | 238-256 | |
| Inorganic Chlorine ppm, = | 5 | |

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China