

Beijing Ranger Chem SM-609R Solid Epoxy Resin

Category : Polymer , Thermoset , Epoxy , Epoxy Cure Resin

Material Notes:

Information provided by Beijing Ranger Chemical Co.

Order this product through the following link:

http://www.lookpolymers.com/polymer_Beijing-Ranger-Chem-SM-609R-Solid-Epoxy-Resin.php

Physical Properties	Metric	English	Comments
Volatiles	<= 0.050 %	<= 0.050 %	

Thermal Properties	Metric	English	Comments
Softening Point	129 - 145 °C	264 - 293 °F	

Optical Properties	Metric	English	Comments
Gardner Color Number	<= 0.50	<= 0.50	

Descriptive Properties	Value	Comments
Epoxy Equivalent g/eq	1800-2500	
Inorganic Chlorine ppm, =	5	
Saponifiable Chlorine ppm, =	100	
Total Chlorine ppm, =	1400	
Viscosity mpa.s/25	Z2-Z5	

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.comEmail : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China