

## Bhansali Engineering Abstron AN-450 Flame Retardant ABS Grade

Category : Polymer , Thermoplastic , ABS Polymer

### Material Notes:

Information provided by Bhansali

Order this product through the following link:

[http://www.lookpolymers.com/polymer\\_Bhansali-Engineering-Abstron-AN-450-Flame-Retardant-ABS-Grade.php](http://www.lookpolymers.com/polymer_Bhansali-Engineering-Abstron-AN-450-Flame-Retardant-ABS-Grade.php)

Physical Properties	Metric	English	Comments
Density	1.17 g/cc	0.0423 lb/in <sup>3</sup>	ASTM D-792
Linear Mold Shrinkage	0.0040 - 0.0060 cm/cm	0.0040 - 0.0060 in/in	ASTM D-955
Melt Flow	63 g/10 min @Load 10.0 kg, Temperature 220 °C	63 g/10 min @Load 22.0 lb, Temperature 428 °F	ASTM D-1238

Mechanical Properties	Metric	English	Comments
Hardness, Rockwell R	106	106	ASTM D-785
Tensile Strength, Yield	41.2 MPa @Thickness 3.20 mm	5970 psi @Thickness 0.126 in	Type 1, 5 mm/min; ASTM D-638
Flexural Yield Strength	56.9 MPa @Thickness 6.40 mm	8250 psi @Thickness 0.252 in	ASTM D-790
Flexural Modulus	2.06 GPa @Thickness 6.40 mm	299 ksi @Thickness 0.252 in	ASTM D-790
Izod Impact, Notched	1.37 J/cm @Thickness 6.40 mm	2.57 ft-lb/in @Thickness 0.252 in	ASTM D-256
	1.76 J/cm @Thickness 3.20 mm	3.31 ft-lb/in @Thickness 0.126 in	ASTM D-256

Thermal Properties	Metric	English	Comments
Deflection Temperature at 1.8 MPa (264 psi)	88.0 °C	190 °F	Method A - Annealed; ASTM D-648
Vicat Softening Point	99.0 °C	210 °F	Method B; ASTM D-1525
Flammability, UL94	V-0 @Thickness 3.20 mm	V-0 @Thickness 0.126 in	UL-94

## **Contact Songhan Plastic Technology Co.,Ltd.**

**Website : [www.lookpolymers.com](http://www.lookpolymers.com)**

**Email : [sales@lookpolymers.com](mailto:sales@lookpolymers.com)**

**Tel : +86 021-51131842**

**Mobile : +86 13061808058**

**Skype : lookpolymers**

**Address : United North Road 215,Fengxian District, Shanghai City,China**