

## Bhansali Engineering Abstron IM17A TT ABS Injection Molding Grade

Category : Polymer , Thermoplastic , ABS Polymer , Acrylonitrile Butadiene Styrene (ABS), Molded

### Material Notes:

High Flow, Medium Impact Information provided by Bhansali

Order this product through the following link:

[http://www.lookpolymers.com/polymer\\_Bhansali-Engineering-Abstron-IM17A-TT-ABS-Injection-Molding-Grade.php](http://www.lookpolymers.com/polymer_Bhansali-Engineering-Abstron-IM17A-TT-ABS-Injection-Molding-Grade.php)

Physical Properties	Metric	English	Comments
Specific Gravity	1.045 g/cc	1.045 g/cc	ASTM D792
Linear Mold Shrinkage	0.00400 - 0.00600 cm/cm	0.00400 - 0.00600 in/in	ASTM D955
Melt Flow	43.0 g/10 min @Load 10.0 kg, Temperature 220 °C	43.0 g/10 min @Load 22.0 lb, Temperature 428 °F	ASTM D1238

Mechanical Properties	Metric	English	Comments
Hardness, Rockwell R	113	113	ASTM D785
Tensile Strength, Yield	42.2 MPa @Thickness 3.20 mm	6120 psi @Thickness 0.126 in	Type I, 5 mm/min; ASTM D638
Flexural Yield Strength	63.7 MPa @Thickness 6.40 mm	9250 psi @Thickness 0.252 in	5 mm/min; ASTM D790
Flexural Modulus	2.16 GPa @Thickness 6.40 mm	313 ksi @Thickness 0.252 in	5 mm/min; ASTM D790
Izod Impact, Notched	1.47 J/cm @Thickness 6.40 mm	2.76 ft-lb/in @Thickness 0.252 in	ASTM D256
	1.67 J/cm @Thickness 3.20 mm	3.12 ft-lb/in @Thickness 0.126 in	ASTM D256

Thermal Properties	Metric	English	Comments
Deflection Temperature at 1.8 MPa (264 psi)	94.0 °C @Thickness 6.40 mm	201 °F @Thickness 0.252 in	Method A; ASTM D648
Flammability, UL94	HB @Thickness 3.20 mm	HB @Thickness 0.126 in	

## **Contact Songhan Plastic Technology Co.,Ltd.**

**Website : [www.lookpolymers.com](http://www.lookpolymers.com)**

**Email : [sales@lookpolymers.com](mailto:sales@lookpolymers.com)**

**Tel : +86 021-51131842**

**Mobile : +86 13061808058**

**Skype : lookpolymers**

**Address : United North Road 215,Fengxian District, Shanghai City,China**