

Bhansali Engineering Abstron IMC-45 FR V2 Flame Retardant PC/ABS Grade

Category : Polymer , Thermoplastic , ABS Polymer , Polycarbonate/ABS Alloy, Unreinforced , Polycarbonate (PC)

Material Notes:

Information provided by Bhansali

Order this product through the following link:

http://www.lookpolymers.com/polymer_Bhansali-Engineering-Abstron-IMC-45-FR-V2-Flame-Retardant-PCABS-Grade.php

Physical Properties	Metric	English	Comments
Density	1.16 g/cc	0.0419 lb/in ³	ASTM D-792
Linear Mold Shrinkage	0.0040 - 0.0060 cm/cm	0.0040 - 0.0060 in/in	ASTM D-955
Melt Flow	30 g/10 min @Load 10.0 kg, Temperature 220 °C	30 g/10 min @Load 22.0 lb, Temperature 428 °F	ASTM D-1238

Mechanical Properties	Metric	English	Comments
Hardness, Rockwell R	114	114	ASTM D-785
Tensile Strength, Yield	49.03 MPa @Thickness 3.20 mm	7112 psi @Thickness 0.126 in	Type 1, 5 mm/min; ASTM D-638
Flexural Yield Strength	68.6 MPa @Thickness 6.40 mm	9960 psi @Thickness 0.252 in	ASTM D-790
Flexural Modulus	2.35 GPa @Thickness 6.40 mm	341 ksi @Thickness 0.252 in	ASTM D-790
Izod Impact, Notched	4.41 J/cm @Thickness 3.20 mm	8.27 ft-lb/in @Thickness 0.126 in	ASTM D-256

Thermal Properties	Metric	English	Comments
Deflection Temperature at 1.8 MPa (264 psi)	96.0 °C	205 °F	Method A - Annealed; ASTM D-648
Vicat Softening Point	105 °C	221 °F	Method B; ASTM D-1525
Flammability, UL94	V-2 @Thickness 3.20 mm	V-2 @Thickness 0.126 in	UL-94

Contact Songhan Plastic Technology Co.,Ltd.Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215, Fengxian District, Shanghai City, China