

Bhansali Engineering Abstron IMGS20 Glass Reinforced Grade

Category : Polymer , Thermoplastic , ABS Polymer

Material Notes:

Glass Reinforced ABS & SAN Resins for product specific requirement of very high rigidity and temperature Information provided by Bhansali

Order this product through the following link:

http://www.lookpolymers.com/polymer_Bhansali-Engineering-Abstron-IMGS20-Glass-Reinforced-Grade.php

Physical Properties	Metric	English	Comments
Density	1.24 g/cc	0.0448 lb/in ³	ASTM D-792
Filler Content	20 %	20 %	Glass
Linear Mold Shrinkage	0.0020 - 0.0040 cm/cm	0.0020 - 0.0040 in/in	ASTM D-955
Melt Flow	16 g/10 min @Load 10.0 kg, Temperature 220 °C	16 g/10 min @Load 22.0 lb, Temperature 428 °F	ASTM D-1238

Mechanical Properties	Metric	English	Comments
Hardness, Rockwell R	118	118	ASTM D-785
Tensile Strength, Yield	73.55 MPa @Thickness 3.20 mm	10670 psi @Thickness 0.126 in	Type 1, 5 mm/min; ASTM D-638
Flexural Yield Strength	98.1 MPa @Thickness 6.40 mm	14200 psi @Thickness 0.252 in	ASTM D-790
Flexural Modulus	4.51 GPa @Thickness 6.40 mm	654 ksi @Thickness 0.252 in	ASTM D-790
Izod Impact, Notched	0.392 J/cm @Thickness 6.40 mm	0.735 ft-lb/in @Thickness 0.252 in	ASTM D-256
	0.588 J/cm @Thickness 3.20 mm	1.10 ft-lb/in @Thickness 0.126 in	ASTM D-256

Thermal Properties	Metric	English	Comments
Deflection Temperature at 1.8 MPa (264 psi)	109 °C	228 °F	Method A - Annealed; ASTM D-648
Vicat Softening Point	120 °C	248 °F	Method B; ASTM D-1525
Flammability, UL94	HB @Thickness 3.20 mm	HB @Thickness 0.126 in	UL-94

Thermal Properties

Metric

English

Comments

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China