

## Bhansali Engineering Abstron MIF-35 ABS Injection Molding Grade

Category : Polymer , Thermoplastic , ABS Polymer

### Material Notes:

High Impact, Medium, High Flow, General Purpose Information provided by Bhansali

Order this product through the following link:

[http://www.lookpolymers.com/polymer\\_Bhansali-Engineering-Abstron-MIF-35-ABS-Injection-Molding-Grade.php](http://www.lookpolymers.com/polymer_Bhansali-Engineering-Abstron-MIF-35-ABS-Injection-Molding-Grade.php)

Physical Properties	Metric	English	Comments
Density	1.045 g/cc	0.03775 lb/in <sup>3</sup>	ASTM D-792
Linear Mold Shrinkage	0.0040 - 0.0060 cm/cm	0.0040 - 0.0060 in/in	ASTM D-955
Melt Flow	38 g/10 min @Load 10.0 kg, Temperature 220 °C	38 g/10 min @Load 22.0 lb, Temperature 428 °F	ASTM D-1238

Mechanical Properties	Metric	English	Comments
Hardness, Rockwell R	110	110	ASTM D-785
Tensile Strength, Yield	44.1 MPa @Thickness 3.20 mm	6400 psi @Thickness 0.126 in	Type 1; ASTM D638
Flexural Yield Strength	63.7 MPa @Thickness 6.40 mm	9250 psi @Thickness 0.252 in	ASTM D790
Flexural Modulus	2.16 GPa @Thickness 6.40 mm	313 ksi @Thickness 0.252 in	ASTM D790
Izod Impact, Notched	2.16 J/cm @Thickness 6.40 mm	4.04 ft-lb/in @Thickness 0.252 in	ASTM D256
	2.549 J/cm @Thickness 3.20 mm	4.775 ft-lb/in @Thickness 0.126 in	ASTM D256

Thermal Properties	Metric	English	Comments
Deflection Temperature at 1.8 MPa (264 psi)	93.0 °C	199 °F	Method A - Annealed; ASTM D-648
Vicat Softening Point	103 °C	217 °F	Method B; ASTM D-1525
Flammability, UL94	HB @Thickness 3.20 mm	HB @Thickness 0.126 in	UL-94

## **Contact Songhan Plastic Technology Co.,Ltd.**

**Website : [www.lookpolymers.com](http://www.lookpolymers.com)**

**Email : [sales@lookpolymers.com](mailto:sales@lookpolymers.com)**

**Tel : +86 021-51131842**

**Mobile : +86 13061808058**

**Skype : lookpolymers**

**Address : United North Road 215,Fengxian District, Shanghai City,China**