

Borealis BD212CF Polypropylene Copolymer

Category : Polymer , Thermoplastic , Polypropylene (PP) , Polypropylene Copolymer

Material Notes:

BD212CF is a heterophasic copolymer. This grade is suitable for the manufacturing of unoriented films on cast and tubular quench film lines. Applications: BD212CF is designed for food packaging, lamination films, stationary films, and label film. Information provided by Borealis AG

Order this product through the following link:

http://www.lookpolymers.com/polymer_Borealis-BD212CF-Polypropylene-Copolymer.php

Physical Properties	Metric	English	Comments
Density	0.900 - 0.910 g/cc	0.0325 - 0.0329 lb/in ³	ISO 1183
Melt Flow	5.0 g/10 min @Load 2.16 kg, Temperature 230 °C	5.0 g/10 min @Load 4.76 lb, Temperature 446 °F	ISO 1133

Mechanical Properties	Metric	English	Comments
Elongation at Break	600 - 800 %	600 - 800 %	ISO 527-3
Tensile Modulus	0.450 - 0.550 GPa	65.3 - 79.8 ksi	ISO 527-2
Flexural Modulus	1.00 GPa	145 ksi	50% relative humidity; ISO 178
Dart Drop, Total Energy	28.0 J @Thickness 0.0500 mm	20.7 ft-lb @Thickness 0.00197 in	1150N; ISO 7765-2
Film Tensile Strength at Break, MD	35.0 - 55.0 MPa	5080 - 7980 psi	ISO 527-3
Film Tensile Strength at Break, TD	30.0 - 50.0 MPa	4350 - 7250 psi	ISO 527-3

Thermal Properties	Metric	English	Comments
Melting Point	158 - 162 °C	316 - 324 °F	DSC; ISO 3146
Vicat Softening Point	145 °C @Load 1.02 kg	293 °F @Load 2.25 lb	ISO 306

Optical Properties	Metric	English	Comments
Haze	<= 25 %	<= 25 %	
Gloss	>= 7.0 %	>= 7.0 %	60° of arc; ASTM D2457

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China