

## Borealis BorPURE™ MB6561 High Density Polyethylene for Injection Molding

Category : Polymer , Thermoplastic , Polyethylene (PE) , HDPE , High Density Polyethylene (HDPE), Injection Molded

### Material Notes:

BorPure™ MB6561 is a bimodal, high-density polyethylene intended for injection and compression molding. This grade combines excellent organoleptic properties, environmental stress crack resistance and superior flow properties with good impact strength even at low temperatures. Applications: caps and closures for beverage food and industrial packaging, transport packaging, consumer and industrial articles for demanding environment. Information provided by Borealis AG

Order this product through the following link:

[http://www.lookpolymers.com/polymer\\_Borealis-BorPURE-MB6561-High-Density-Polyethylene-for-Injection-Molding.php](http://www.lookpolymers.com/polymer_Borealis-BorPURE-MB6561-High-Density-Polyethylene-for-Injection-Molding.php)

Physical Properties	Metric	English	Comments
Density	0.955 g/cc	0.0345 lb/in <sup>3</sup>	ISO 1183
Environmental Stress Crack Resistance	180 hour	180 hour	Igepal 10%, F50; ASTM D1693-A
Linear Mold Shrinkage	0.010 - 0.020 cm/cm	0.010 - 0.020 in/in	
Melt Flow	1.5 g/10 min @Load 2.16 kg, Temperature 190 °C	1.5 g/10 min @Load 4.76 lb, Temperature 374 °F	ISO 1133

Mechanical Properties	Metric	English	Comments
Tensile Strength, Yield	23.0 MPa	3340 psi	50mm/min; ISO 527-2
Elongation at Yield	10 %	10 %	50mm/min; ISO 527-2
Tensile Modulus	0.900 GPa	131 ksi	1mm/min; ISO 527-2

Processing Properties	Metric	English	Comments
Melt Temperature	190 - 250 °C	374 - 482 °F	
Mold Temperature	10.0 - 40.0 °C	50.0 - 104 °F	

Descriptive Properties	Value	Comments
Full Notch Creep-Test (hours)	13	6 MPa, 50°C, Arcopal N110 2%, ISO/DIS 16700-2000
Injection Velocity	highest possible	

## Contact Songhan Plastic Technology Co.,Ltd.

Website : [www.lookpolymers.com](http://www.lookpolymers.com)

Email : [sales@lookpolymers.com](mailto:sales@lookpolymers.com)

**Tel : +86 021-51131842**

**Mobile : +86 13061808058**

**Skype : lookpolymers**

**Address : United North Road 215,Fengxian District, Shanghai City,China**