

Borealis BorPURE™ RJ377MO Polypropylene, Transparent Random Copolymer

Category : Polymer , Thermoplastic , Polypropylene (PP) , Polypropylene Copolymer

Material Notes:

BorPure™ RJ377MO is a specially modified high MFR transparent polypropylene random copolymer based on proprietary Borealis Nucleation Technology (BNT), with an excellent organoleptic performance. No tainting of taste & odor of food products and a faster crystallization speed offer benefits towards all parts of the value chain. It is designed for high-speed injection molding and contains nucleating and demolding additives. Applications: closures, lids, pails, and square containers. Information provided by Borealis AG

Order this product through the following link:

http://www.lookpolymers.com/polymer_Borealis-BorPURE-RJ377MO-Polypropylene-Transparent-Random-Copolymer.php

Physical Properties	Metric	English	Comments
Density	0.905 g/cc	0.0327 lb/in ³	ISO 1183
Melt Flow	45 g/10 min @Load 2.16 kg, Temperature 230 °C	45 g/10 min @Load 4.76 lb, Temperature 446 °F	ISO 1133

Mechanical Properties	Metric	English	Comments
Tensile Strength, Yield	27.0 MPa	3920 psi	50mm/min; ISO 527-2
Elongation at Yield	13 %	13 %	50mm/min; ISO 527-2
Tensile Modulus	1.05 GPa	152 ksi	1mm/min; ISO 527-3
Charpy Impact, Notched	0.500 J/cm ² @Temperature 23.0 °C	2.38 ft-lb/in ² @Temperature 73.4 °F	ISO 179/1eA

Thermal Properties	Metric	English	Comments
Deflection Temperature at 0.46 MPa (66 psi)	73.0 °C	163 °F	ISO 75-2

Optical Properties	Metric	English	Comments
Transmission, Visible	90 %	90 %	transparent; thickness not quantified

Contact Songhan Plastic Technology Co.,Ltd.Website : www.lookpolymers.comEmail : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215, Fengxian District, Shanghai City, China