

## Borealis Bormed™ RD808CF Polypropylene Random Copolymer

Category : Polymer , Thermoplastic , Polypropylene (PP) , Polypropylene Copolymer

### Material Notes:

Bormed™ RD808CF is a random copolymer. Applications: Bormed™ RD808CF is intended for packaging for medical devices, thin pouches, and packaging for pharmaceutical products. Additives: Bormed™ RD808CF contains no slip, antiblock, antistatic additives or nucleating additives. Information provided by Borealis AG

Order this product through the following link:

[http://www.lookpolymers.com/polymer\\_Borealis-Bormed-RD808CF-Polypropylene-Random-Copolymer.php](http://www.lookpolymers.com/polymer_Borealis-Bormed-RD808CF-Polypropylene-Random-Copolymer.php)

Physical Properties	Metric	English	Comments
Density	0.905 g/cc	0.0327 lb/in <sup>3</sup>	ISO 1183
Melt Flow	8.0 g/10 min @Load 2.16 kg, Temperature 230 °C	8.0 g/10 min @Load 4.76 lb, Temperature 446 °F	ISO 1133

Mechanical Properties	Metric	English	Comments
Tensile Modulus	0.400 GPa	58.0 ksi	MD/TD; ISO 527-3
Flexural Modulus	0.700 GPa	102 ksi	50% humidity; ISO 178
Dart Drop, Total Energy	30.0 J @Thickness 0.0500 mm	22.1 ft-lb @Thickness 0.00197 in	1100N; ISO 7765-2
Film Tensile Strength at Break, MD	30.0 MPa	4350 psi	ISO 527-3
Film Tensile Strength at Break, TD	30.0 MPa	4350 psi	ISO 527-3

Thermal Properties	Metric	English	Comments
Melting Point	140 °C	284 °F	DSC; ISO 3146
Deflection Temperature at 0.46 MPa (66 psi)	60.0 °C	140 °F	ISO 75-2
Vicat Softening Point	125 °C @Load 1.02 kg	257 °F @Load 2.25 lb	ISO 306

Optical Properties	Metric	English	Comments
Haze	<= 1.0 %	<= 1.0 %	ASTM D1003
Gloss	>= 150 %	>= 150 %	20° of arc; ASTM D2457

## **Contact Songhan Plastic Technology Co.,Ltd.**

**Website : [www.lookpolymers.com](http://www.lookpolymers.com)**

**Email : [sales@lookpolymers.com](mailto:sales@lookpolymers.com)**

**Tel : +86 021-51131842**

**Mobile : +86 13061808058**

**Skype : lookpolymers**

**Address : United North Road 215,Fengxian District, Shanghai City,China**