

Borealis Borsoft™ SD200CF High Impact Polypropylene Random Heterophasic Copolymer for Cast Film

Category : Polymer , Film , Thermoplastic , Polypropylene (PP) , Polypropylene, Impact Modified; Molded/Extruded

Material Notes:

Borsoft SD200CF is a very soft random heterophasic copolymer, suitable for use on chill roll process. The product combines unique softness with outstanding mechanical properties making it the ideal solution for mono and coex film design. Borsoft SD200CF is especially suitable for stationery folders, food/textile packaging, technical films, property modification in other applications fields, substitution of other plastics, and hygienic films. Information provided by the Manufacturer.

Order this product through the following link:

http://www.lookpolymers.com/polymer_Borealis-Borsoft-SD200CF-High-Impact-Polypropylene-Random-Heterophasic-Copolymer-for-Cast-Film.php

Physical Properties	Metric	English	Comments
Density	0.900 - 0.910 g/cc	0.0325 - 0.0329 lb/in ³	ISO 1183
Thickness	50.0 microns	1.97 mil	
Melt Flow	9.0 g/10 min @Load 2.16 kg, Temperature 230 °C	9.0 g/10 min @Load 4.76 lb, Temperature 446 °F	ISO 1133

Mechanical Properties	Metric	English	Comments
Film Elongation at Break, MD	650 %	650 %	ISO 527-3
Film Elongation at Break, TD	850 %	850 %	ISO 527-3
Flexural Modulus	0.450 GPa	65.3 ksi	ISO 178
Secant Modulus, MD	0.200 GPa	29.0 ksi	ISO 527-3
Secant Modulus, TD	0.300 GPa	43.5 ksi	ISO 527-3
Impact	57.5	57.5	Dynatest, Damaging Force (N); ISO 7765-2
Impact Test	1.60 J	1.18 ft-lb	Dynatest, Penetration Energy; ISO 7765-2
Film Tensile Strength at Break, MD	30.0 - 50.0 MPa	4350 - 7250 psi	ISO 527-3
Film Tensile Strength at Break, TD	25.0 - 45.0 MPa	3630 - 6530 psi	ISO 527-3

Thermal Properties	Metric	English	Comments
Melting Point	140 - 144 °C	284 - 291 °F	ISO 3146
Vicat Softening Point	115 °C	239 °F	A (10N); ISO 306

Optical Properties	Metric	English	Comments
Haze	8.0 %	8.0 %	ASTM D1003
	<= 8.0 %	<= 8.0 %	ASTM D1003
Gloss	>= 20 %	>= 20 %	ASTM D2457

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China