

## Borealis FA7224 Low Density Polyethylene

Category : Polymer , Thermoplastic , Polyethylene (PE) , LDPE , Low Density Polyethylene (LDPE), Film Grade

### Material Notes:

FA7224 has been developed for applications such as: Thin bags with excellent optical and slip properties, and laundry and other textile bags. Contains antioxidant. Information provided by Borealis AG

Order this product through the following link:

[http://www.lookpolymers.com/polymer\\_Borealis-FA7224-Low-Density-Polyethylene.php](http://www.lookpolymers.com/polymer_Borealis-FA7224-Low-Density-Polyethylene.php)

Physical Properties	Metric	English	Comments
Density	0.922 g/cc	0.0333 lb/in <sup>3</sup>	ISO 1183
Melt Flow	4.0 g/10 min @Load 2.16 kg, Temperature 190 °C	4.0 g/10 min @Load 4.76 lb, Temperature 374 °F	ISO 1133
Antiblock Level	1100 ppm	1100 ppm	talc; Borealis Method
Slip Level	700 ppm	700 ppm	erucamide; Borealis Method

Mechanical Properties	Metric	English	Comments
Film Elongation at Break, MD	400 %	400 %	ISO 527-3
Film Elongation at Break, TD	650 %	650 %	ISO 527-3
Tensile Modulus	0.180 GPa	26.1 ksi	TD; ASTM D882-A
	0.200 GPa	29.0 ksi	MD; ASTM D882-A
Coefficient of Friction	0.15	0.15	Dynamic; ISO 8295
Elmendorf Tear Strength, MD	7.65 g/micron	194 g/mil	ISO 6383/2
Elmendorf Tear Strength, TD	5.097 g/micron	129.5 g/mil	ISO 6383/2
Dart Drop Test	80.0 g @Thickness 0.0400 mm	0.176 lb @Thickness 0.00157 in	ISO 7765-1
Film Tensile Strength at Break, MD	20.0 MPa	2900 psi	ISO 527-3
Film Tensile Strength at Break, TD	18.0 MPa	2610 psi	ISO 527-3

Thermal Properties	Metric	English	Comments
Melting Point	111 °C	232 °F	ISO 11357-3
Vicat Softening Point	94.0 °C	201 °F	ISO 306

Thermal Properties	Metric	English	Comments
Optical Properties	Metric	English	Comments
Haze	6.0 %	6.0 %	ASTM D1003
Gloss	110 %	110 %	ASTM D2457

Processing Properties	Metric	English	Comments
Melt Temperature	140 - 180 °C	284 - 356 °F	

## Contact Songhan Plastic Technology Co.,Ltd.

Website : [www.lookpolymers.com](http://www.lookpolymers.com)

Email : [sales@lookpolymers.com](mailto:sales@lookpolymers.com)

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China