

Borealis FR4832 Chemically Crosslinkable Polyethylene Compound for Primary Automotive Wires

Category : Polymer , Thermoplastic , Polyethylene (PE)

Material Notes:

FR4832 is a Chemically Crosslinkable Polyethylene Compound for Primary Automotive Wires. Applications: FR4832 is intended for use as a 125° C rated primary insulation for crosslinked automotive wire. Specifications FR4832 in combination meets the requirements when processed using sound extrusion and testing procedure: SAE J1128/J1127. Information provided by Borealis AG

Order this product through the following link:

http://www.lookpolymers.com/polymer_Borealis-FR4832-Chemically-Crosslinkable-Polyethylene-Compound-for-Primary-Automotive-Wires.php

Physical Properties	Metric	English	Comments
Density	1.40 g/cc	0.0506 lb/in ³	ASTM D792

Mechanical Properties	Metric	English	Comments
Hardness, Shore D	50	50	ASTM D2240
Tensile Strength at Break	13.8 MPa	2000 psi	
	17.25 MPa	2502 psi	ASTM D412
Elongation at Break	200 %	200 %	ASTM D412

Thermal Properties	Metric	English	Comments
Brittleness Temperature	<= -50.0 °C	<= -58.0 °F	ASTM D2863
Oxygen Index	25 %	25 %	ASTM D2863

Electrical Properties	Metric	English	Comments
Volume Resistivity	1.00e+6 ohm-cm	1.00e+6 ohm-cm	ASTM D257
Dielectric Constant	3.7	3.7	ASTM D150
	@Frequency 6.00e+7 Hz	@Frequency 6.00e+7 Hz	
Dielectric Strength	>= 21.7 kV/mm	>= 551 kV/in	ASTM D149
Dissipation Factor	0.010	0.010	ASTM D150
	@Frequency 6.00e+7 Hz	@Frequency 6.00e+7 Hz	

Processing Properties	Metric	English	Comments
-----------------------	--------	---------	----------

Processing Properties	55.0 °C Metric	131 °F English	humidified air drying temperature;2- Comments
Middle Barrel Temperature	96.0 °C	205 °F	barrel 1
	110 °C	230 °F	barrel 6
Melt Temperature	120 - 125 °C	248 - 257 °F	
Shelf Life	12.0 Month	12.0 Month	

Descriptive Properties	Value	Comments
Single Vertical Flame Test	Pass	20AWG;ISO 6722/SAE J1128

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China