

Borealis LE0315-99 Polyethylene Thermoplastic Semiconductive Compound

Category : Polymer , Thermoplastic , Polyethylene (PE)

Material Notes:

LE0315-99 has the same melt flow properties as the peroxide containing material. Application: LE0315-99 is used during start up of a triple-head line. It helps to use a non-peroxide containing material until stable conditions are reached. The settings should be the same as for the peroxide containing compound. Information provided by Borealis AG

Order this product through the following link:

http://www.lookpolymers.com/polymer_Borealis-LE0315-99-Polyethylene-Thermoplastic-Semiconductive-Compound.php

Physical Properties	Metric	English	Comments
Density	1.17 g/cc	0.0423 lb/in ³	ASTM D792

Electrical Properties	Metric	English	Comments
Volume Resistivity	50 ohm-cm	50 ohm-cm	ASTM D991
	@Temperature 23.0 °C	@Temperature 73.4 °F	
	90 ohm-cm	90 ohm-cm	ASTM D991
	@Temperature 90.0 °C	@Temperature 194 °F	

Processing Properties	Metric	English	Comments
Shelf Life	12.0 Month	12.0 Month	

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China