

Borealis RB307MO Polypropylene Random Copolymer

Category : Polymer , Thermoplastic , Polypropylene (PP) , Polypropylene Copolymer

Material Notes:

RB307MO is a random copolymer with good transparency and contact clarity, very good gloss and surface finish. This grade also features high heat distortion temperature. Applications: household and chemical containers such as detergents, cleaners, motor oils, industrial chemicals, and cosmetics. Information provided by Borealis AG

Order this product through the following link:

http://www.lookpolymers.com/polymer_Borealis-RB307MO-Polypropylene-Random-Copolymer.php

Physical Properties	Metric	English	Comments
Density	0.902 g/cc	0.0326 lb/in ³	ISO 1183
Melt Flow	1.5 g/10 min @Load 2.16 kg, Temperature 230 °C	1.5 g/10 min @Load 4.76 lb, Temperature 446 °F	ISO 1133

Mechanical Properties	Metric	English	Comments
Tensile Strength, Yield	24.0 MPa	3480 psi	50mm/min; ISO 527-2
Elongation at Yield	13 %	13 %	50mm/min; ISO 527-2
Tensile Modulus	0.900 GPa	131 ksi	1mm/min; ISO 527-2
Charpy Impact, Notched	2.00 J/cm ² @Temperature 23.0 °C	9.52 ft-lb/in ² @Temperature 73.4 °F	ISO 179/1eA

Thermal Properties	Metric	English	Comments
Deflection Temperature at 0.46 MPa (66 psi)	80.0 °C	176 °F	ISO 75-2

Processing Properties	Metric	English	Comments
Middle Barrel Temperature	190 - 220 °C	374 - 428 °F	
Die Temperature	180 - 220 °C	356 - 428 °F	
Melt Temperature	180 - 220 °C	356 - 428 °F	

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.comEmail : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215, Fengxian District, Shanghai City, China