

## Borealis RJ370MO Polypropylene, Transparent Random Copolymer

Category : Polymer , Thermoplastic , Polypropylene (PP) , Polypropylene Copolymer

### Material Notes:

RJ370MO is a specially modified highly-transparent polypropylene random copolymer with very high melt flow rate. It is designed for high-speed injection molding and contains nucleating and demolding additives. Additivation has been optimized to provide good antistatic and demolding properties without blooming or plate-out problems. This polymer is a CR (controlled rheology) grade with narrow molecular weight distribution giving low warpage. Products originating from this grade have excellent transparency, good organoleptic properties, good balance of stiffness and impact strength at ambient temperatures. Applications: lids, square containers, square boxes, and closures. Information provided by Borealis AG

Order this product through the following link:

[http://www.lookpolymers.com/polymer\\_Borealis-RJ370MO-Polypropylene-Transparent-Random-Copolymer.php](http://www.lookpolymers.com/polymer_Borealis-RJ370MO-Polypropylene-Transparent-Random-Copolymer.php)

Physical Properties	Metric	English	Comments
Density	0.905 g/cc	0.0327 lb/in <sup>3</sup>	ISO 1183
Linear Mold Shrinkage	0.010 - 0.020 cm/cm	0.010 - 0.020 in/in	
Melt Flow	45 g/10 min @Load 2.16 kg, Temperature 230 °C	45 g/10 min @Load 4.76 lb, Temperature 446 °F	ISO 1133

Mechanical Properties	Metric	English	Comments
Hardness, Rockwell R	80	80	ISO 2039-2
Tensile Strength, Yield	27.0 MPa	3920 psi	50mm/min; ISO 527-2
Elongation at Yield	13 %	13 %	50mm/min; ISO 527-2
Tensile Modulus	1.05 GPa	152 ksi	1mm/min; ISO 527-2
Charpy Impact, Notched	0.500 J/cm <sup>2</sup> @Temperature 23.0 °C	2.38 ft-lb/in <sup>2</sup> @Temperature 73.4 °F	ISO 179/1eA

Thermal Properties	Metric	English	Comments
Deflection Temperature at 0.46 MPa (66 psi)	73.0 °C	163 °F	ISO 75-2

Optical Properties	Metric	English	Comments
Transmission, Visible	90 %	90 %	transparent; thickness not quantified

Processing Properties	Metric	English	Comments
-----------------------	--------	---------	----------

Melt Temperature Processing Properties	210 - 260 °C Metric	410 - 500 °F English	Comments
Mold Temperature	15.0 - 40.0 °C	59.0 - 104 °F	
Hold Pressure	20.0 - 50.0 MPa	2900 - 7250 psi	

Descriptive Properties	Value	Comments
Injection Velocity	high	

## Contact Songhan Plastic Technology Co.,Ltd.

Website : [www.lookpolymers.com](http://www.lookpolymers.com)

Email : [sales@lookpolymers.com](mailto:sales@lookpolymers.com)

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China