

Borealis Visico™ LE4423/LE4437 Scorch Retardant, Moisture-Crosslinking Polyethylene Compound for Low Voltage Installation

Category : Polymer , Thermoplastic , Polyethylene (PE) , LDPE , Low Density Polyethylene (LDPE), Wire/Cable Grade

Material Notes:

Visico LE4423/LE4437 is a mature, moisture-induced crosslinking polyethylene compound that is designed for use as low voltage wire insulation and jacketing. The combination of a Visico base material, LE4423, and a tin catalyst masterbatch, LE4437 provides a highly scorch retardant compound with excellent thermal stability. LE4432/LE4437 contains a patented scorch retardant additive (SRA) that increases the processing window for a moisture crosslinking compound and minimizes the tendency for premature crosslinking in the extruder, head of die. LE4437 should be added to LE4432 directly in the extruder hopper by dry blending at a ratio of 5 parts LE4437 to 95 parts LE4423. LE4423/LE4437 is recommended for use as insulation for low voltage control cables and power cables up to 6 kV in rating. Information provided by the Manufacturer.

Order this product through the following link:

http://www.lookpolymers.com/polymer_Borealis-Visico-LE4423LE4437-Scorch-Retardant-Moisture-Crosslinking-Polyethylene-Compound-for-Low-Voltage-Installation.php

Physical Properties	Metric	English	Comments
Density	0.923 g/cc	0.0333 lb/in ³	LE 4423; ASTM D792
	0.941 g/cc	0.0340 lb/in ³	LE 4437; ASTM D792
Melt Flow	0.90 g/10 min	0.90 g/10 min	LE 4423; ASTM D1238

Mechanical Properties	Metric	English	Comments
Tensile Strength, Yield	>= 13.28 MPa	>= 1926 psi	Heat Aging (7 days at 121°C); ASTM D412
	14.8 MPa	2140 psi	ASTM D412
Elongation at Break	<= 50 %	<= 50 %	Hot Creep Test (150°C, .2 MPa); ICEA T-28-562
	270 %	270 %	Heat Aging (7 days at 121°C); ASTM D412
	300 %	300 %	ASTM D412
Tensile Set	<= 5.0 %	<= 5.0 %	Hot Creep Test (150°C, .2 MPa); ICE T-28-562

Electrical Properties	Metric	English	Comments
Electrical Resistivity	1.00e+16 ohm-cm	1.00e+16 ohm-cm	ASTM D257
Dielectric Constant	2.3	2.3	ASTM D150
	@Frequency 60 Hz	@Frequency 60 Hz	
Dielectric Strength	>= 21.7 kV/mm	>= 550 kV/in	ASTM D149

Electrical Properties	Metric	English	Comments
Dissipation Factor	@Frequency 60 Hz	@Frequency 60 Hz	ASTM D150

Processing Properties	Metric	English	Comments
Middle Barrel Temperature	>= 171 °C	>= 340 °F	
Front Barrel Temperature	>= 146 °C	>= 295 °F	
Die Temperature	>= 177 °C	>= 350 °F	
Head Temperature	>= 177 °C	>= 351 °F	

Descriptive Properties	Value	Comments
Horizontal Flame Test	Pass	14AWG-30mil, UL 1581

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China