

BorsodChem ONGRONAT CR-30-40 MDI Isocyanate

Category : Polymer

Material Notes:

Description of product: Polymethylene-polyphenyl-isocyanate, 4,4-diphenyl-methane-diisocyanate (MDI) and mixture of its higher functionality, multi-ring oligomers. Field of application: With suitable polyols it can be used as isocyanate component for producing rigid, semi-rigid insulating foams. Information provided by BorsodChem Rt.

Order this product through the following link:

http://www.lookpolymers.com/polymer_BorsodChem-ONGRONAT-CR-30-40-MDI-Isocyanate.php

Physical Properties	Metric	English	Comments
Viscosity	350 - 450 cP	350 - 450 cP	
	@Temperature 25.0 °C	@Temperature 77.0 °F	

Chemical Properties	Metric	English	Comments
Acid Value	<= 0.050	<= 0.050	wt %

Processing Properties	Metric	English	Comments
Processing Temperature	20.0 - 25.0 °C	68.0 - 77.0 °F	

Descriptive Properties	Value	Comments
Hydrolyzable chlorine	0.3 max wt%	
NCO Content, wt%	30 - 32	

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.comEmail : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215, Fengxian District, Shanghai City, China