

## BorsodChem ONGROSTYR F-II Expandable Polystyrene (EPS)

Category: Polymer, Thermoplastic, Polystyrene (PS), Expanded Polystyrene (EPS)

## **Material Notes:**

ONGROSTYR F-II is an expandable, flame-retardant styrene homopolymer, produced by suspension polymerization. The product meets the requirements of DIN 4102 and of B1 class of building materials, i.e. "low inflammability grade". Field of application: ONGROSTYR F-II is suitable for traditional and vacuum molded processing. The minimum apparent density of the end-product is 15 kg/m3. This type is recommended for insulation in the building industry and for industrial packaging. It is not for food packaging, when it is in direct contact with the food. Information provided by BorsodChem Rt.

## Order this product through the following link:

http://www.lookpolymers.com/polymer\_BorsodChem-ONGROSTYR-F-II-Expandable-Polystyrene-EPS.php

| Physical Properties   | Metric             | English                            | Comments                                |
|-----------------------|--------------------|------------------------------------|---|
| Apparent Bulk Density | 0.550 - 0.650 g/cc | 0.0199 - 0.0235 lb/in <sup>3</sup> | MSZ ISO 60:1994                         |
| Particle Size         | 710 - 1000 μm      | 710 - 1000 μm                      | min 92%; BC HSZ 326:2001/1<br>screening |
| Viscosity             | 1.7 cP             | 1.7 cP                             | Ubbelohde viscosity meter               |

| Descriptive Properties            | Value     | Comments |
|-----------------------------------|-----------|----------|
| Blowing agent content (pentane),% | 5.5 - 6.5 |          |
| Residual Monomer Content max %    | 0.2       |          |
| Water Content, %, max             | 1.4       |          |

## Contact Songhan Plastic Technology Co.,Ltd.

Website: www.lookpolymers.com Email: sales@lookpolymers.com

Tel: +86 021-51131842 Mobile: +86 13061808058

Skype: lookpolymers

Address: United North Road 215, Fengxian District, Shanghai City, China