

## **Braskem D080T Homopolymer Polypropylene**

Category: Polymer, Thermoplastic, Polypropylene (PP)

## **Material Notes:**

Description: Excellent Melt Stability, General Purpose Injection MoldingApplications: Suggested Uses Include Patio Furniture, Closures, Staple FibersThis resin meets the requirements for olefin polymers as defined in 21 CFR, section 177.1520 issued by the Food and Drug

Administration. The additives present are covered in appropriate regulation by FDA.Information provided by Braskem

## Order this product through the following link:

http://www.lookpolymers.com/polymer\_Braskem-D080T-Homopolymer-Polypropylene.php

Physical Properties	Metric	English	Comments
Melt Flow	8.0 g/10 min	8.0 g/10 min	ASTM D1238
	@Load 2.16 kg, Temperature 230 °C	@Load 4.76 lb, Temperature 446 °F	

Mechanical Properties	Metric	English	Comments
Hardness, Rockwell R	106	106	ASTM D785
Tensile Strength	37.2 MPa	5400 psi	2 in/min; ASTM D638
Elongation at Yield	9.0 %	9.0 %	2 in/min; ASTM D638
Flexural Modulus	1.59 GPa	230 ksi	0.05 in/min, 1% secant; ASTM D-790A
Izod Impact, Notched	0.320 J/cm	0.600 ft-lb/in	ASTM D256A

## **Contact Songhan Plastic Technology Co.,Ltd.**

Website: www.lookpolymers.com Email: sales@lookpolymers.com

Tel: +86 021-51131842 Mobile: +86 13061808058

Skype: lookpolymers

Address: United North Road 215, Fengxian District, Shanghai City, China