

## Braskem F2523 Blown Film Extrusion Low Density Polyethylene

Category : Polymer , Film , Thermoplastic , Polyethylene (PE) , LDPE , Low Density Polyethylene (LDPE), Film Grade

**Material Notes:**

Automatic packaging for several products; High transparency films. Additives: Antiblock, DInformation provided by Braskem.

Order this product through the following link:

[http://www.lookpolymers.com/polymer\\_Braskem-F2523-Blown-Film-Extrusion-Low-Density-Polyethylene.php](http://www.lookpolymers.com/polymer_Braskem-F2523-Blown-Film-Extrusion-Low-Density-Polyethylene.php)

Physical Properties	Metric	English	Comments
Specific Gravity	0.923 g/cc	0.923 g/cc	ASTM D1505/D792
Thickness	25.0 microns	0.984 mil	
Melt Flow	2.5 g/10 min @Load 2.16 kg, Temperature 190 °C	2.5 g/10 min @Load 4.76 lb, Temperature 374 °F	ASTM D1238

Mechanical Properties	Metric	English	Comments
Film Elongation at Break, MD	230 %	230 %	ASTM D882
Film Elongation at Break, TD	930 %	930 %	ASTM D882
Elmendorf Tear Strength TD	110 g	110 g	gF; ASTM D1922
Dart Drop Test	60.0 g	0.132 lb	gF/50%f; ASTM D1709
Film Tensile Strength at Break, MD	30.0 MPa	4350 psi	ASTM D882
Film Tensile Strength at Break, TD	20.0 MPa	2900 psi	ASTM D882

Optical Properties	Metric	English	Comments
Haze	6.0 % @Thickness 0.0250 mm	6.0 % @Thickness 0.000984 in	ASTM D1003
Gloss	110 % @Thickness 0.0250 mm	110 % @Thickness 0.000984 in	60°; ASTM D2457

## Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215, Fengxian District, Shanghai City, China