

Braskem FF018F Homopolymer Polypropylene

Category : Polymer , Thermoplastic , Polypropylene (PP)

Material Notes:

Description: Excellent Color and Processing Stability, Superior Optical and Mechanical Properties, Broad Processing Window Applications:

Suggested Uses Include BOPP Applications This resin meets the requirements for olefin polymers as defined in 21 CFR, section 177.1520 issued by the Food and Drug Administration. The additives present are covered in appropriate regulation by FDA. Information provided by

Braskem

Order this product through the following link:

http://www.lookpolymers.com/polymer_Braskem-FF018F-Homopolymer-Polypropylene.php

Physical Properties	Metric	English	Comments
Melt Flow	1.8 g/10 min @Load 2.16 kg, Temperature 230 °C	1.8 g/10 min @Load 4.76 lb, Temperature 446 °F	ASTM D1238

Mechanical Properties	Metric	English	Comments
Tensile Strength	33.8 MPa	4900 psi	2 in/min; ASTM D638
Flexural Modulus	1.31 GPa	190 ksi	0.05 in/min, 1% secant; ASTM D-790A
Izod Impact, Notched	0.267 J/cm	0.500 ft-lb/in	ASTM D256A

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215, Fengxian District, Shanghai City, China