

## Braskem Green PE SLL318 Blow Film Extrusion and Cast Film Extrusion Linear Low Density Polyethylene

**Category :** Polymer , Film , Renewable/Recycled Polymer , Thermoplastic , Polyethylene (PE) , LLDPE , Linear Low Density Polyethylene (LLDPE), Film Grade

### Material Notes:

Description: SLL118 is a Linear Low Density Polyethylene, copolymer of butene-1. Developed for blown film extrusion in blends with polyethylenes. Films obtained with this product show a good processing performance balanced with good optical and mechanical properties as well as sealability. Very low gel amount. It contains antioxidant additives. The minimum biobased content of this grade is 87%, determined according to ASTM D6866. Applications: Stretch films; liners; LDPE and HDPE blends and packages for general use. Others applications: blends for irrigation pipes. Information provided by Braskem.

Order this product through the following link:

[http://www.lookpolymers.com/polymer\\_Braskem-Green-PE-SLL318-Blow-Film-Extrusion-and-Cast-Film-Extrusion-Linear-Low-Density-Polyethylene.php](http://www.lookpolymers.com/polymer_Braskem-Green-PE-SLL318-Blow-Film-Extrusion-and-Cast-Film-Extrusion-Linear-Low-Density-Polyethylene.php)

Physical Properties	Metric	English	Comments
Specific Gravity	0.918 g/cc	0.918 g/cc	ASTM D1505/D792
Thickness	25.0 microns	0.984 mil	
Melt Flow	2.7 g/10 min @Load 2.16 kg, Temperature 190 °C	2.7 g/10 min @Load 4.76 lb, Temperature 374 °F	ASTM D1238

Mechanical Properties	Metric	English	Comments
Film Elongation at Break, MD	1220 %	1220 %	ASTM D882
Film Elongation at Break, TD	1440 %	1440 %	ASTM D882
Elmendorf Tear Strength MD	120 g	120 g	gF; ASTM D1922
Elmendorf Tear Strength TD	340 g	340 g	gF; ASTM D1922
Dart Drop Test	90.0 g	0.198 lb	g/F50; ASTM D1709
Film Tensile Strength at Break, MD	30.0 MPa	4350 psi	ASTM D882
Film Tensile Strength at Break, TD	30.0 MPa	4350 psi	ASTM D882
1% Secant Modulus, MD	180 MPa	26100 psi	ASTM D882
1% Secant Modulus, TD	200 MPa	29000 psi	ASTM D882

## Contact Songhan Plastic Technology Co.,Ltd.

Website : [www.lookpolymers.com](http://www.lookpolymers.com)

Email : [sales@lookpolymers.com](mailto:sales@lookpolymers.com)

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China