

## Braskem H 152 Fiber Extrusion Polypropylene

Category : Polymer , Thermoplastic , Polypropylene (PP) , Polypropylene, Extrusion Grade

**Material Notes:**

Applications: Nonwoven by blow process for disposable diapers, personal care and disposable medical care. Information provided by Braskem

Order this product through the following link:

[http://www.lookpolymers.com/polymer\\_Braskem-H-152-Fiber-Extrusion-Polypropylene.php](http://www.lookpolymers.com/polymer_Braskem-H-152-Fiber-Extrusion-Polypropylene.php)

Physical Properties	Metric	English	Comments
Density	0.905 g/cc	0.0327 lb/in <sup>3</sup>	ASTM D792A
Melt Flow	1100 g/10 min @Load 2.16 kg, Temperature 230 °C	1100 g/10 min @Load 4.76 lb, Temperature 446 °F	ASTM D1238L

Mechanical Properties	Metric	English	Comments
Hardness, Rockwell R	98	98	ASTM D785
Flexural Modulus	1.40 GPa	203 ksi	ASTM D790
Izod Impact, Notched	0.110 J/cm @Temperature 23.0 °C	0.206 ft-lb/in @Temperature 73.4 °F	ASTM D256A

Thermal Properties	Metric	English	Comments
Deflection Temperature at 0.46 MPa (66 psi)	98.0 °C	208 °F	ASTM D648
Deflection Temperature at 1.8 MPa (264 psi)	58.0 °C	136 °F	ASTM D648
Vicat Softening Point	149 °C	300 °F	-1kg; ASTM D1525

## Contact Songhan Plastic Technology Co.,Ltd.

Website : [www.lookpolymers.com](http://www.lookpolymers.com)Email : [sales@lookpolymers.com](mailto:sales@lookpolymers.com)

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China